

Fundamentals of Polymer Physics

Bincai (Pun Choi) LI



Chemical Industry Press

Fundamentals of Polymer Physics

Bincai (Pun Choi) LI

Chemical Industry Press

• Beijing •

(京) 新登字 039 号

图书在版编目 (CIP) 数据

高分子物理基础: 英文/李斌才著. —北京: 化学工业出版社, 1999.3
ISBN 7-5025-2472-X

I. 高… II. 李… III. 高聚物物理学-英文 IV. 0631

中国版本图书馆 CIP 数据核字 (1999) 第 03022 号

Copyright © 1997 by Chemical Industry Press. All rights reserved. No part of this book may be reproduced by any means, or transmitted, or translated into a machine language without the written permission of the copyright owner.

Address:

Pun Choi LI
Flt-C, 3/F, Nan Chang House
Tsuen Wan Centre, Tsuen Wan
N.T., Hong Kong
Tel: 24980505
Fax: + 852-2498-0505 or + 852-2498-0046

Fundamentals of Polymer Physics

Bincai (Pun Choi) LI 著

责任编辑: 虞 旻

责任校对: 陶燕华

封面设计: 蒋艳君

*

化学工业出版社出版发行

(北京市朝阳区惠新里 3 号 邮政编码 100029)

新华书店北京发行所经销

北京市雅昌印刷有限公司印刷

三河市东柳装订厂装订

*

开本 787×1092 毫米 1/16 印张 26 字数 768 千字

1999 年 6 月第 1 版 1999 年 6 月北京第 1 次印刷

ISBN 7-5025-2472-X/TQ·1117

定 价: 60.00 元

版权所有 违者必究

该书如有缺页、倒页、脱页者, 本社发行部负责调换

PREFACE TO THE ENGLISH EDITION

The Chinese Edition of the Book was published by the Science Press, Beijing, in the late of 1989, entitled "Structure and Physical Properties of High Polymers". Since then, the Book was rewritten in English with revisions and enlargements. In the writings, emphases have been laid on improving the deepness and comprehensibility of the Book and adding new contents to keep up with the developments in polymer science. Some essential contents are cited as examples: Discussions on NMR begin with basic principles and the advanced techniques, pFT and MAS, are introduced. In the descriptions of amorphous bulk polymers, the method of RDF, in addition to SANS, is also described so that different scalings can be compared. The application of SALS to the studies of crystal structure and birefringence is set forth. Recent progresses in the field of polymer blends are discussed. Comprehensive discussions on the molecular theory of rubber elasticity are set forth; besides the classical affine network, the phantom and the constrained junction models are also expounded, moreover, birefringence and SANS of deformed networks are described. Two molecular theories of viscoelasticity, the bead and spring and the reptation models, are discussed, which concern with the rheological behavior of polymers. Fractography is introduced associated with fracture of polymers. Most of the key Equations in the Text are derived in details for instructive purpose, e. g., the radial distribution function of chain coils, the kinetic equation of crystallization, the elastic equation of state for polymer networks, etc. Furthermore, Study Problems appended to the end of each Chap. are instructive and helpful to reviewing.

Since the Book covers almost the entire field of polymer physics, expounding most of the basic principles, and moreover, it is addressed to students of polymer science, the change of the Title to the present one, "Fundamentals of Polymer Physics", is appropriate. The treatment of the Book is at the first year graduate (or last year undergraduate) level as a textbook. However, a reminiscence of the fundamental concepts and basic principles would also be helpful to research workers and engineers in the field of polymer science and industry.

Bincai (Pun Choi) LI
李斌才

PREFACE TO THE CHINESE EDITION

The importance of the subject, structure and physical properties of high polymers, in the field of polymer science should be stressed unambiguously since this subject concerns with almost every aspect of the field: from the monitoring of polymerization reactions to the characterization of the products, from the control of the processability of raw materials to the prediction and judgement of the quality of finished articles; all of these courses involve the studies of the relationships between structure and properties. Moreover, research works in this subject contribute to the advances of the theories of polymer science. However, the concerned works published in our country in the seventies were rare. At the beginning of the eighties, the author had written a series of papers of the same title, published successively in the Journal of Synthetic Rubber Industry [1]. Afterwards, some books of similar kind were published [2 ~ 8]. Beginning from 1983, the author opened the course, "Structure and Behavior of High Polymers", in South China University of Science and Technology to graduate students of polymer science. The same course was also offered twice to Qing Tao College of Chemical Engineering in Summer vacations. Then, stemming from some monographs of polymer physics and following the advances in polymer science, the book was begun to prepare for the purpose of providing a new text for graduate students as well as a reference for research workers and engineers in the field of polymer science and industry. In view of that students in their undergraduate studies would be in contact with all the basic knowledges of polymer science, the author had no attempt to write a book of all-embracing but rather more insight and detailed discussions on key topics.

A high polymer consists of macromolecules each of which is formed by linking together one kind (or two or three kinds in copolymer) of monomeric (structural) units of the same chemical structure but not necessarily the same configuration. Therefore, the studies of the chemical structure, configuration, and arrangement of monomeric units have become the foundation of polymer science. Studies in this respect have been greatly promoted by the method of nuclear magnetic resonance since the seventies, so that detailed discussions on NMR spectroscopy are given in Chapter 2. The variations of the conformations of molecular chains due to internal rotations about single bonds relate in many respects to the behavior of polymers such as crystallization, properties of solution and molecular mass determination, long range elasticity, as well as the viscoelastic flow of the bulk. Details of conformations are described in Chaps. 3 and 4. The manifestations of bulk properties in the performances of polymers depend on the structure of aggregation states and the molecular motions in different physical states. Orientation of molecular chains in the aggregation state and the glassy-rubbery transition of the physical state are two characteristics of high polymers which are not displayed by low molecular substances; and the two transition temperatures, T_g and T_m , are particularly important in the commercial applications of polymers. These phenomena are discussed in Chaps. 6 and 8. Long range elasticity arising from the change of conformational entropy of molecular chains, which is indispensable for rubbers, is introduced in Chap. 9. The properties most closely related to the practical applications of high polymers are mechanical properties which, according to the author's idea, are best divided into two parts: 1) visco-elastic properties and flow behavior governing the processability of polymeric materials [Chap. 10] and 2) strength and failure of polymer products including fracture mechanics and the micromechanism of failure such as shear yielding and crazing [Chap. 11]. For many years, polymer blends because of their variety and versatility have played an important role in open up the uses of polymers, a review is given in Chapter 7. However, the book is no more inclusive, some important topics have been omitted, for example, electric and optical properties.

In view of that the uses of units for the expressions of the magnitudes of physical quantities have not

reached to the common standards of SI and many non-SI units are also prevailing in recent literatures, conversion tables for non-SI and SI units are given in Appendix I. Appendix II is a list of abbreviations for polymers.

The author is especially indebted to Professor Jianyuan Pan of Zhong Shan University, Professor Min Zhu and Professor Yuanlan Jiang of South China University of Science and Technology for their readings and valuable criticisms to the manuscripts, and Mr. Licheng Jia and Miss Ying Liu for their transcription of the manuscripts.

Bincai (Pun Choi) LI

李斌才

May, 1988

- [1] Bincai Li, "Structure and Physical Properties of High Polymers", (A Lecture Series in Chinese), J. of Synthetic Rubber Industry, 1980 No. 1 to 1981 No. 2.
- [2] Jianyuan Pan, Shiping Xi, and Shaohui Huang, "Polymer Physics", (in Chinese), Guang Dong Pubs. of Science and Technology, Guangzhou, 1982.
- [3] Junman He, Weixiao Chen, and Xixia Dong, "Polymer Physics", (in Chinese), Fu Dan University Press, Shanghai, 1982.
- [4] Laboratory of Polymer Physics, China University of Science and technology, "Structure and Behavior of High Polymers", (in Chinese), Scientific Pubs., Beijing, 1983.
- [5] R. B. Seymour and C. E. Carraher, "Structure-Property Relationships in Polymers". Plenum Press, New York, 1984.
- [6] J. E. Mark, A. Eisenberg, W. W. Graessley, Leo Mandelkern, and L. L. Koenig, "Physical Properties of Polymers", Am. Chem. Soc., Washington D. C., 1984.
- [7] Hans Georg Elias, "Macromolecules 1, Structure and Properties", 2nd Ed., Plenum Press, New York, 1984.
- [8] L. H. Sperling, "Introduction to Physical Polymer Science", John-Wiley & Sons, Inc., New York, 1986.

CONTENTS

1. Introduction	1
Study Problems	4
2. Structure and Arrangement of Monomeric Units	5
2.1 Monomer and Structure of Monomeric Unit	5
2.2 The Ways of Connection between Monomeric Units	8
2.3 The Asymmetric Carbon in a Monomeric Unit	11
2.4 Structure of Monomeric Units of Unsaturated Carbon Chains	13
2.5 Arrangement of Monomeric Units in Copolymers (Sequence Structure)	14
2.6 Studies of the Structure and Arrangement of Monomeric Units by Nuclear Magnetic Resonance (NMR) Spectroscopy	16
2.6.1 Principles	16
2.6.2 Experimental Methods	18
2.6.3 Analysis of the NMR Spectra	19
2.6.3.1 Chemical Shift and the Position of the Absorption Line	19
2.6.3.2 Intensity of the Absorption Peak	20
2.6.3.3 Spin-Spin Coupling	21
2.6.3.4 NMR Spectra of ^{19}F and ^{13}C	22
2.6.3.5 Pulsed Fourier Transform (PFT) NMR Spectroscopy	23
2.6.4 Studies of the Short Range Structure of Polymers by NMR Spectroscopy	24
2.6.4.1 Determination of Head-to-Head Connection between Monomeric Units of Fluorine Containing Polymers	25
2.6.4.2 Statistical Analysis of Sequence Structure	26
2.6.4.3 Analysis of the ^{13}C NMR Spectra of Polypropylene	30
2.6.5 Solution NMR and Solid State NMR	33
Study Problems	34
Main Symbols	35
References	36
3. Conformation of Molecular Chains in the Crystalline State	37
3.1 Internal Rotation of Molecules and Rotational Isomers	37
3.2 Conformation of Saturated Carbon Chains in the Crystalline State	39
3.3 Conformation of Unsaturated Carbon Chains in the Crystalline State	41
3.4 Conformation of Hetero-Chain in the Crystalline State	43
Study Problems	45
References	46
4. Conformation of Molecular Chain in Dilute Solution	47
4.1 The Random Coil	47
4.2 Conformation of Real Molecular Chain	51
4.3 Interaction between Polymer and Solvent	55
4.3.1 Properties of Dilute Polymer Solutions	55
4.3.2 Theory of Lattice Model	56
4.3.3 Flory's Theory of Equation of State	62
4.4 Relationship between the Intrinsic Viscosity of Polymer and the Conformation of the Chain Coil	64

4.5	Conformation of Branched Molecular Chain	67
	Study Problems	71
	Main Symbols	72
	References	74
5.	Molecular Mass and Molecular Mass Distribution	76
5.1	Average Molecular Mass	76
5.2	Relationship between the Intrinsic Viscosity of Polymer and Molecular Mass	77
5.2.1	Determination of Intrinsic Viscosity	77
5.2.2	The Relationship between Molecular Mass and Intrinsic Viscosity	79
5.3	Determination of Number-Average Molecular Mass by Osmometry	81
5.4	Determination of Mass-Average Molecular Mass and Size and Shape of Gel Coils by the Method of Light Scattering	83
5.5	Determination of Molecular Mass by Ultracentrifuge-Sedimentation	86
5.5.1	Sedimentation Velocity	87
5.5.2	Estimation of the Size of Macromolecular Coils in Solution	90
5.5.3	Sedimentation-Diffusion Equilibrium	91
5.6	Fractionation of Polymer and Molecular Mass Distribution	91
5.7	Determination of Molecular Mass Distribution by Gel Permeation Chromatography (GPC)	95
5.7.1	Experimental Method and Treatment of Data	95
5.7.2	Some Particular Techniques in GPC	98
	Study Problems	100
	Main Symbols	101
	References	103
6.	The Aggregation States of Polymers	104
6.1	Cohesive Energy Density and Solubility Parameter	104
6.2	The Aggregation States and the Physical States of High Polymers	106
6.3	Structure Models for the Amorphous State	107
6.4	Structure and Morphology of Crystalline Polymers	114
6.4.1	Single Crystals Grown from Polymer Solutions (the Lamellae)	114
6.4.2	Spherulites Grown from Bulk Crystallized Polymers	115
6.4.3	Morphologies Other Than Spherulites	120
6.4.4	Determination of Crystallinity	122
6.5	The Process of Polymer Crystallization	123
6.5.1	Formation of Nuclei	123
6.5.2	Growth of Crystals or Spherulites	124
6.5.3	Overall Crystallization Kinetics	125
6.6	Crystallization of High Polymers under Dynamic Conditions	130
6.7	Orientation in High Polymers and Measurement of Anisotropy	131
6.7.1	Acoustic Method	133
6.7.2	Birefringence	133
6.7.3	X-Ray Diffraction	136
6.7.4	Dichroism	136
6.7.5	Anisotropy of Mechanical Properties	137
6.8	Structure and Properties of Liquid Crystals	138
6.8.1	Thermotropic Liquid Crystals	138
6.8.2	Lyotropic Liquid Crystals	139
	Study Problems	141

Main Symbols	142
References	143
7. Polymer Blends, Thermodynamics and Morphology	145
7.1 Introductory Remarks	145
7.2 Thermodynamics of Blends and Polymer-Polymer Miscibility	146
7.2.1 $\Delta H_M \geq 0$	147
7.2.2 $\Delta H_M < 0$ and Specific Interactions (SI)	151
7.2.3 Equation of State Theory	155
7.2.4 Determination of the Interaction Parameters	157
7.2.4.1 Measurements of the Heat of Mixing	157
7.2.4.2 Measurements of the Chemical Potential Difference of a Solvent in a Ternary System	159
7.2.4.3 Combination of Segmental Interaction Parameters in Homopolymer/Copolymer Blends	160
7.3 Experimental Criteria for Miscibility	160
7.3.1 Glass Transition Temperature, T_g	161
7.3.1.1 Some Examples and Results of Testings	161
7.3.1.2 Phase Dimensions and the Probe Size of a Test Method	163
7.3.1.3 The T_g -Composition Equations for Miscible Blends	165
7.3.2 Mutual Solvent	168
7.3.3 Optical Clarity	168
7.3.4 Small Angle Neutron Scattering, SANS	169
7.3.5 Pulsed Nuclear Magnetic Resonance	172
7.3.6 Ultrasonic Velocity	174
7.3.7 Fluorescence Emission Spectroscopy	175
7.4 Phase Diagram and Phase Separation	176
7.4.1 Methods for the Determination of Phase Diagram	176
7.4.1.1 The Cloud Point Method (Turbidity Measurement)	176
7.4.1.2 Measurements of T_g	178
7.4.2 Various Types of Phase Diagrams	178
7.4.3 Mechanism of Phase Separation	181
7.4.3.1 Phase Separation by Nucleation and Growth	181
7.4.3.2 Phase Separation by Spinodal Decomposition	182
7.4.3.3 Examples of Phase Separation	183
7.5 Investigations of Heterogeneous Polymer Blends	184
7.5.1 Studies of Morphology by Means of Microscopy	184
7.5.2 Measurements of Inhomogeneity via Small Angle X-Ray Scattering, SAXS	186
7.6 The Interface between two Phases	189
7.6.1 Determination of Interfacial Tension and Surface Tension of Polymers	189
7.6.2 Theories of Interfacial Tension	190
7.6.3 Adhesion Between two Phases	192
7.6.4 Compatibilization of Polymer Blends	194
7.7 Polymer Blends Containing Crystallizable Components	196
7.7.1 Crystalline-Amorphous Polymer Blends	196
7.7.1.1 Crystallizability of the Crystallizable Component	196
7.7.1.2 Melting Point Depression and the Determination of χ_{12}	197
7.7.1.3 Rate of Crystallization	197
7.7.1.4 Morphology of the Crystalline-Amorphous Polymer Blends	198

7.7.2 Crystalline-Crystalline Polymer Blends	200
Study Problems	201
Main Symbols	202
References	204
8. The Thermal Properties of High Polymers	206
8.1 Molecular Mass and Transitions of Physical States	206
8.2 Determination of Glass Transition Temperature T_g	207
8.2.1 Dilatometry (and Refractometry)	207
8.2.2 Enthalpy Measurements: DTA and DSC	208
8.2.3 Dynamic Mechanical Thermal Analysis, DMTA	208
8.2.3.1 Free Oscillation	209
8.2.3.2 Forced Oscillation	210
8.2.3.3 Activation Energy of the Relaxation Process	212
8.2.3.4 Multiple Transitions in Polymers (Mechanical Spectroscopy)	212
8.2.4 Dielectric Relaxation	214
8.2.5 Nuclear Magnetic Resonance	215
8.3 The Free Volume Theory of Glass Transition	216
8.4 The Effect of Structure on T_g	221
8.4.1 The Flexibility of the Main Chain and the Bulkiness of Rigid Side Groups	221
8.4.2 The Geometric Configuration of the Monomeric Units	222
8.4.3 Plasticization of Plasticizers and Internal Plasticization of Flexible Side Chains	223
8.4.4 Interactions between Molecular Chains	224
8.4.5 The T_g of Copolymers	226
8.4.6 The Effects of Molecular Mass, Cross-Linking, and Branching	227
8.5 The Transition Temperatures of Crystalline Polymers	228
8.6 The Process of Melting and the Melting Point T_m of High Polymers	229
8.7 The Determination of T_m and Some Related Transitions	231
8.7.1 Dilatometry	231
8.7.2 Thermal Analysis: DTA and DSC	231
8.7.2.1 DTA	231
8.7.2.2 DSC	231
8.7.3 Determination via DMTA	233
8.8 Effect of Structure on T_m	233
8.9 Transition Temperatures and the Applications of Polymeric Materials	234
8.10 Thermal Conductivity and Thermal Stability	236
8.10.1 Thermal Conductivity	236
8.10.2 Thermal Stability	237
8.10.2.1 Thermal Stability with Respect to Dimension	237
8.10.2.2 Thermal Stability with Respect to Resistance to Decomposition (Pyrolysis)	238
Study Problems	239
Main Symbols	240
References	241
9. Polymer Networks and Rubber Elasticity	243
9.1 The Formation of Polymer Networks	243
9.2 Thermodynamics of Rubber Elasticity	245
9.2.1 Isochoral Process	245
9.2.2 Isobaric Process	247

9.2.3	Results of Measurements	248
9.3	Structure of Polymer Networks and Method of Characterization	250
9.4	Molecular (or Statistical) Theory of Rubber Elasticity	252
9.4.1	The Affine Network Model	252
9.4.2	The Phantom Network Model	255
9.4.3	The Constrained Junction Model	256
9.4.4	Deformations Other Than Uniaxial	260
9.4.4.1	Biaxial Extension	260
9.4.4.2	Pure Shear	261
9.4.4.3	Simple Shear	261
9.4.5	Non-Gaussian Chain Statistics	261
9.5	Phenomenological (or Continuum) Theory of Rubber Elasticity	262
9.6	Syntheses of Networks of Pre-designed Structure via End-linking Reactions and Their Applications	266
9.6.1	Network Perfectness and Ultimate Properties	268
9.6.2	The Upturn Problem	269
9.7	Swelling of Polymer Networks and Determination of Degree of Cross-linking	271
	Study Problems	275
	Main Symbols	277
	References	278
10.	Mechanical Properties of High Polymers	
I	Viscoelastic Properties and Rheological Behaviours	279
10.1	The Deformation of High Polymers	279
10.1.1	Deformation of Perfect Elastic Solids (Reversible)	279
10.1.2	Deformation of Ideal Viscous Fluids (Irreversible)	280
10.1.3	Mechanical Properties Reflected in Uniaxial Extension	281
10.2	Linear Viscoelasticity and Phenomenological Studies	283
10.2.1	Creep	284
10.2.2	Stress Relaxation	285
10.2.3	Dynamic Mechanical Properties	287
10.2.4	Distribution of Relaxation Times and Boltzmann Superposition Principle	292
10.2.5	Time-Temperature Equivalence and Superposition	293
10.3	Rheology of High Polymers, Viscosity and Flow	296
10.3.1	Cone-and-Plate Viscometer	298
10.3.2	Capillary Rheometer	299
10.3.2.1	Relationship between Viscosity and Shear Rate, the Flow Curve	301
10.3.2.2	Die Swell and Normal Stress Difference	302
10.3.2.3	Appearance of the Extrudates and Melt Fracture	303
10.3.3	Extensional (or Elongational) Flow and Extensional Viscosity	304
10.4	External and Internal Factors That Govern the Viscoelastic and Rheological Behaviors of Polymers	308
10.4.1	Temperature	308
10.4.2	Strain Rate	309
10.4.3	Molecular Mass, Molecular Mass Distribution, and Branching	310
10.4.4	Chemical Structure	315
10.5	Molecular Theories of Viscoelasticity	315
10.5.1	Bead and Spring Model after Rouse and Bueche	315
10.5.2	Reptation Model after de Gennes and Dio-Edwards	318

Study Problems	320
Main Symbols	322
References	323
11. Mechanical Properties of High Polymers	
II Strength and Failure	325
11.1 Laboratory Tests for Mechanical Strength	325
11.1.1 Uniaxial Tensile Test and Compression	325
11.1.2 Shear Strength	328
11.1.3 Fatigue Resistance	328
11.1.4 Impact Resistance	330
11.1.4.1 Pendulum Impact, Izod and Charpy Tests	331
11.1.4.2 Tensile Impact Test	333
11.1.4.3 Impact Test by Free Falling Pendulum	334
11.2 Analysis of Mechanical Strength	334
11.2.1 States of Stress	334
11.2.2 Deformation of Materials and Stress-Strain Relationship	338
11.2.3 Considere's Plot	339
11.2.4 Brittle-Ductile Transition of Polymeric Materials	339
11.3 Fracture on the Atomic and Molecular Level	340
11.3.1 Theoretical Strength of Solids	341
11.3.2 The Kinetic Theory of Fracture	343
11.3.3 Experimental Methods for the Study of Molecular Fracture	344
11.3.3.1 Electron Spin Resonance, ESR	344
11.3.3.2 Infra-red Spectroscopy	347
11.3.3.3 Small Angle X-ray Scattering, SAXS	348
11.4 Fracture Mechanics of High Polymers	348
11.4.1 Linear Elastic Fracture Mechanics (LEFM) and Griffith Equation	349
11.4.2 Another Meaning of G_c and Method of Determination	352
11.4.3 Stress-Intensity Factor K	354
11.4.4 The Size of Plastic Zone	355
11.4.5 Thickness Effect and Fracture Toughness	356
11.4.6 Non-linear Elastoplastic Fracture Mechanics (NEFM)	358
11.5 Shear Yielding and Crazing	358
11.5.1 Theories and Criteria of Shear Yielding	362
11.5.1.1 Theory of Viscous Flow	362
11.5.1.2 Molecular Mechanism	362
11.5.1.3 Yield Criteria	363
11.5.2 Inhomogeneous Deformation and Shear Bands	364
11.5.3 Brittle vs. Ductile, Crazing vs. Shear Yielding	366
11.5.4 The Microstructure of a Craze and Micromechanics	366
11.5.5 The Initiation and Growth of a Craze	369
11.5.6 Craze Breakdown and the Propagation of a Crack	371
11.6 Fractography and Fracture Mechanism of Polymeric Materials	372
11.6.1 Morphology of Fracture Surfaces	372
11.6.2 Crack Propagation and Strain Distribution around a Crack Tip	374
11.6.3 Mechanical Hysteresis and Surface Roughness	375
11.6.4 Fatigue Failure, Mechanism and Fractography	377
11.6.4.1 Fatigue Failure of Plastics	377

11.6.4.2 Fatigue Failure of Cross-linked Rubbers	379
Study Problems	380
Main Symbols	382
References	384
Appendix	386
I Conversion Tables for SI and non-SI Units	386
II Abbreviations for Polymers	387
Index	389

1. Introduction

Polymer chemistry has been stemming from organic chemistry. High polymers, most of which are organic compounds with chain-like molecules, may simply be classified according to the chemical nature of their molecular chains, see Table 1.1. Thus, the nomenclature of high polymers is based on the structure of their macromolecular chains. For homopolymers, each chain is formed by linking together structural units of the same chemical structure know as MONOMERIC UNITS, but a monomeric unit may assume different configurations. For example, there are three stereo-isomers for monomeric units of polybutadiene: *cis*-, *trans*-, and 1,2-. For copolymers, a chain is formed by two or three kinds of monomeric units. The studies of the structure, configuration, and arrangement of monomeric units have become the foundation of polymer science. Refer to Chap. 2.

Table 1.1 Classification of High Polymers

Type		Example
Carbon Chain Polymer	Saturated	Polyethylene $\text{-(CH}_2\text{--CH}_2\text{)}_n$
	Unsaturated	Polybutadiene $\text{-(CH}_2\text{--CH=CH--CH}_2\text{)}_n$
Hetero-chain Polymer		Nylon-6,6 $\text{-(CO(CH}_2\text{)}_4\text{CO--NH(CH}_2\text{)}_6\text{NH)}_n$

The most important characteristic of high polymers is the great magnitude and inhomogeneity of their molecular masses which can only be expressed as average quantities. The molecular mass must reach a certain value for a high polymer to possess physical properties which low molecular mass substances do not display, particularly mechanical properties. This TRANSITION MOLECULAR MASS is about 150000 ~ 200000 for non-polar carbon chain polymers. For example, the molecular mass of butyl rubber has to exceed 200000 for a vulcanizate to have a usable break strength, see Fig. 1.1. For polar hetero-chain polymers, the transition molecular mass can be much lower, being 15000 ~ 20000, because the interactions between molecular chains are strengthened by polar groups or hydrogen bondings.




Fig. 1.1 Relationship between molecular mass of butyl rubber and the break strength of its vulcanizate.


Macromolecular chains are not necessarily linear, some of them assume branched or other shapes. Fig. 1.2 presents different shapes of polymer molecules, therein (3) is a polymer stereo-network which is formed by cross-linking together many molecular chains. Such a network is insoluble in any solvent, molecular mass is not determinable by usual methods so that the concept of molecule is no more applicable. (5) and (6) in the Fig. are folded and helical chains, respectively, existing in the crystalline regions of some polymer bulks; they will become randomly coiled linear molecules when melted or dissolved in solvents.

Most polymers are soluble in certain solvents. Therefore, informations concerning the structure of individual molecules such as molecular mass, molecular mass distribution, molecular shapes (e. g., branching), etc., can be obtained from the studies of the properties of dilute polymer solutions. These studies have become an important field in polymer science, see Chaps. (4) and (5).

(1) linear molecule



(4) ladder molecule




(2) branched molecule



(5) folded chain



(3) polymer network



(6) helical chain




Fig. 1.2 Some geometrical shapes of polymer molecules [(3) is an infinite network, the concept of molecule is not applicable].

Practically, polymers are used in the form of bulks; it is necessary to study the relationship between structure and bulk properties. Of course, the structures of monomeric units and individual molecules are of fundamental. For example, poly(α -methylstyrene) has a much higher glass transition temperature T_g than polystyrene, since the methyl groups in the monomeric units increase the stiffness of the chain. Rubber of too low a molecular mass couldn't yield a vulcanizate with sufficient strength because of the incompleteness of the network, see Fig. 1.1. However, the aggregation state (amorphous or crystalline) of the bulk plays an important role; in many cases, the effect of the structure of monomeric unit on bulk properties is via its effect on the aggregation state. The example of polyethylene is cited. Its molecular chains are regular with no substituents so that liable to close together for crystallization, and high crystallinity in the bulk prevents PE for application as rubber. Copolymerization of ethylene and propylene results in molecular chains of irregular structure which prohibit crystallization, and the copolymer produced (with low T_g) has become a famous commercial rubber. For some crystalline polymers used as plastics such as PE and PP, molecular mass and its distribution may influence the rate and degree of crystallization, while the structure of the crystalline region would in turn influence the mechanical properties of the bulk. Therefore, structure of aggregation state is directly related to bulk properties, its importance is unquestionable.

Most polymers consist of chain molecules. But some of them have to be transformed into stereo-networks for commercial applications. A typical example is rubber which must be vulcanized in order to possess long range elasticity and strength. other examples are phenol-formaldehyde resin and epoxides.

The role of molecular motion in the relationship between structure and physical properties should not be ignored. For a rubber in the course of processing, the molecular mass of which should not be too high and process oil has to be added in order to promote molecular flow so that the 'compound' would have sufficient plasticity for fabrication. However, once network is formed by vulcanization, no relative motions among molecules take place so that the product is stable in shape; but chain segments in the network can be set into motion for elasticity.

Thermoplastics melt and relative molecular motions (flow) can be set in at high temperature for processing such as extrusion or moulding. Once cooling down to room temperature, the properties of the products depend on the nature of the monomeric units of the polymers. For polymers with monomeric units forming irregular chain structure and T_g higher than room temperature, such as atactic polystyrene and poly(methyl methacrylate), they are in a state of amorphous glass with molecular motions frozen,

displaying a hard and brittle property. For crystalline polymers (whose monomeric units form regular chain structure) such as PE and PP, crystallites of high melting point are dispersed in amorphous matrix which is rubbery at room temperature due to low T_g . There would be no molecular motion in the crystalline region, but motions of chain segments in the rubbery matrix can be set in. Therefore, impact energy could be transformed into energy of molecular motions when the bulk is under the action of impact. These polymers display a property of toughness.

The scope of polymer structure is demonstrated in Fig. 1.3.




Fig. 1.3 Aspects in the studies of polymer structure, (PMMA, poly(methyl methacrylate); SBR, styrene-butadiene rubber; PE, polyethylene; PP, polypropylene).

The physical properties of polymer bulks have to be interpreted in terms of structures. For example, glass transition temperature and melting point are related to the structure of molecular chains and that of the aggregation state. But in turn, the result of the study of structure needs demonstration and proof from physical properties. The structure of the aggregation state revealed by X-ray diffraction, electron microscopy, etc. should be expounded via physical properties. For example, crystallinity must be associ-

ated with melting point. Thus, structure and physical properties are always correlated.

Problems in the production of polymers lie on the studies of structure and physical properties, such as to establish various methods of characterization to monitor the processing behavior of raw materials and the qualities of final products. These studies at the same time, promote the advancement of the theories of polymer science. The relationships are shown in Fig. 1.4.




Fig. 1.4 Relationships between structure and physical properties.

Study Problems

- I-1 What is meant by transition molecular mass? The transition molecular mass for Nylon-6,6 is much lower than that for polybutadiene, why?
- I-2 Give one example to illustrate how the structure of aggregation state is related to the mechanical properties of the polymer.