

Green Energy and Technology

Carlo Pellegrino
Flora Faleschini

Sustainability Improvements in the Concrete Industry

Use of Recycled Materials for Structural
Concrete Production

 Springer

Carlo Pellegrino · Elora Faleschini

Sustainability Improvements in the Concrete Industry

Use of Recycled Materials for Structural
Concrete Production

Carlo Pellegrino
Department of Civil, Environmental
and Architectural Engineering
University of Padua
Padua
Italy

Flora Faleschini
Department of Civil, Environmental
and Architectural Engineering
University of Padua
Padua
Italy

ISSN 1865-3529
Green Energy and Technology
ISBN 978-3-319-28538-2
DOI 10.1007/978-3-319-28540-5

ISSN 1865-3537 (electronic)
ISBN 978-3-319-28540-5 (eBook)

Library of Congress Control Number: 2016950883

© Springer International Publishing Switzerland 2016

This work is subject to copyright. All rights are reserved by the Publisher, whether the whole or part of the material is concerned, specifically the rights of translation, reprinting, reuse of illustrations, recitation, broadcasting, reproduction on microfilms or in any other physical way, and transmission or information storage and retrieval, electronic adaptation, computer software, or by similar or dissimilar methodology now known or hereafter developed.

The use of general descriptive names, registered names, trademarks, service marks, etc. in this publication does not imply, even in the absence of a specific statement, that such names are exempt from the relevant protective laws and regulations and therefore free for general use.

The publisher, the authors and the editors are safe to assume that the advice and information in this book are believed to be true and accurate at the date of publication. Neither the publisher nor the authors or the editors give a warranty, express or implied, with respect to the material contained herein or for any errors or omissions that may have been made.

Printed on acid-free paper

This Springer imprint is published by Springer Nature
The registered company is Springer International Publishing AG
The registered company address is: Gewerbestrasse 11, 6330 Cham, Switzerland

List of Figures

Figure 2.1	Scheme of a C&DWs treatment plant	10
Figure 2.2	Recycled concrete aggregate	16
Figure 2.3	Steel slag production in Europe [72]	20
Figure 2.4	Slag cooling	22
Figure 2.5	Light-brown FA and dark-grey FA	29
Figure 3.1	Comparison of Newtonian, shear-thickening and shear-thinning fluids	36
Figure 3.2	Newton's equation for a viscous fluid: F is the shear force (N), A is the area of the plane parallel to the applied force (m^2), τ is the shear stress (Pa), η is the viscosity (Pa s), $\partial u/\partial z$ is the velocity gradient, equal to the shear rate $\dot{\gamma}(s^{-1})$	36
Figure 3.3	Slump test	48
Figure 3.4	Penetrating rod test methods: Kelly-ball and Vicat apparatus	49
Figure 3.5	Experimental apparatus for evaluating filling ability of fresh concretes.	50
Figure 3.6	ConTec BML Viscometer	53
Figure 3.7	Sampling profile using a ConTec BML viscometer for evaluating Bingham parameters of fresh recycled aggregate concrete with 35 % RA	54
Figure 3.8	Viscometric measurement of fresh recycled concrete with 35 % RCA and $w/c = 0.4$	58
Figure 3.9	Schematic representation of plug flow (from [46]) and its influence on a viscometric measurement performed on fresh recycled concrete with 35 % RCA and $w/c = 0.4$	59
Figure 3.10	Iterative procedure applied to extract Bingham rheology with plug state at plug flow boundary R_s (from [46])	60

Figure 3.11	The use of rheographs for highlighting the effect of adding water, water-reducing admixture (WRA), air-entrainer admixture (AEA) and silica fume (SF) on Bingham parameters (adapted from [50])	61
Figure 3.12	Recycled aggregates with high attached mortar content.	63
Figure 3.13	<i>Left</i> RAC20/0.4-1 %WRA; <i>Right</i> EMV20/0.4-1 %WRA	68
Figure 3.14	Effect of WRA content, substitution ration and aggregates proportioning method ($w/c = 0.4$)	69
Figure 3.15	Effect of WRA content, substitution ration and aggregates proportioning method ($w/c = 0.5$)	70
Figure 3.16	Scatter plot and distribution of residuals of theoretical and experimental slump value according to Murata and Kukawa relation	71
Figure 3.17	Scatter plot and distribution of residuals of theoretical and experimental slump value according to de Larrad relation	72
Figure 4.1	Electric arc furnace slag vs. siliceous aggregates.	78
Figure 4.2	SEM-BSE image of the cross section of the slag aggregate (from [4])	81
Figure 4.3	Aggregates grading curves.	84
Figure 4.4	Splitting surfaces of the concretes with EAF slag	86
Figure 4.5	SEM-BSE image of the efflorescence + EDS spectrum	88
Figure 4.6	Disposition of steel reinforcement in the cross-section of the beams (from [12])	92
Figure 4.7	Disposition of steel reinforcement in type A beams (from [12])	93
Figure 4.8	Load versus deflection at midspan diagrams for type A beams (from [12])	94
Figure 4.9	Load versus crack width diagrams for type A beams (from [12])	94
Figure 4.10	Crack patterns in RC structural elements after bending failure (from [12])	94
Figure 4.11	Bending failure: concrete cracking in A1 beams	95
Figure 4.12	Bending failure: concrete crushing in A2 beams	95
Figure 4.13	Load versus deflection at midspan diagrams for type B beams (from [12])	96
Figure 4.14	Load versus crack width diagrams for type B beams (from [12])	96
Figure 4.15	Crack patterns in RC structural elements after shear failure (from [12])	96
Figure 4.16	Shear failure in B2 beams	97
Figure 4.17	Cubic compressive strength of the examined concretes	100
Figure 4.18	Tensile strength of the examined concretes	101
Figure 4.19	Splitting failures of two HPC concretes.	101

Figure 4.20	Elastic modulus of the examined concretes (from [4]).	102
Figure 4.21	Ordinary performance concrete: conventional (a) and EAF (b); High performance concrete: conventional (c) and EAF (d).	103
Figure 5.1	Life Cycle Assessment phases.	112
Figure 5.2	Land quality evolution: transformation and occupation effects (adapted from [32])	118
Figure 5.3	Block diagram of the activities in the analyzed quarry (from [39])	121
Figure 5.4	Block diagram of the activities in the treatment plant of EAF aggregates (from [39])	125
Figure 5.5	The effect of system boundaries expansion on carbon emissions for aggregates productive chains. Upper: transportation emission per unit mass; transportation per unit volume.	131
Figure 5.6	The effect of system boundaries expansion on carbon emissions for concrete production. Transportation emissions are expressed per unit volume of concrete.	132
Figure 5.7	Extraction and imports rate of natural aggregate in the analyzed territory [43].	134
Figure 5.8	Temporal evolution of I/DMC in the analyzed territory [43]	135
Figure 5.9	Quarry exhaustion time: ER stands for extraction rate, t_R is the exhaustion time	137

List of Tables

Table 2.1	CDWs European production [17].	8
Table 2.2	Acceptance criteria for RA according to German standards	11
Table 2.3	Substitution ratio (in % by volume) according to EN 206-1 [29] and DIN 1045-2 [30].	12
Table 2.4	Maximum allowable quantity of RA in concrete according to Italian normative	13
Table 2.5	Acceptance criteria for RA according to Japanese standards	14
Table 2.6	Classification of recycled aggregate according to Portuguese normative	14
Table 2.7	Physical properties of steel slag.	24
Table 2.8	Chemical composition of EAF slag	24
Table 3.1	One-parameter test methods for the assessment of fresh concrete properties	47
Table 3.2	Main physical properties of aggregates used (from [46]).	66
Table 3.3	Mix design of the concrete analyzed (from [46]).	67
Table 3.4	Results of slump test	68
Table 4.1	Shape of EAF aggregates (from [12])	79
Table 4.2	Physical properties of EAF slag (coarse fraction)	80
Table 4.3	Physical properties of EAF slag (fine fraction) [13].	80
Table 4.4	Physical properties of aggregates (from [12])	82
Table 4.5	Mixture details (from [12])	83
Table 4.6	Physical properties of aggregates (from [13])	83
Table 4.7	Mixture details (from [13])	84
Table 4.8	Results of the slump test (from [13]).	85
Table 4.9	Mechanical properties of concretes (from [12])	85
Table 4.10	Mechanical properties of concretes (from [13])	86
Table 4.11	Compressive strength in specimens after accelerated ageing for 32 days (from [13])	89

Table 4.12	Compressive strength in specimens after accelerated ageing for 32 days plus weathering for 90 days (from [13]).	90
Table 4.13	Compressive strength in specimens after freezing/thawing cycles for 25 days (from [13]).	90
Table 4.14	Compressive strength in specimens wetting/drying cycles for 30 days (from [13])	91
Table 4.15	Experimental and theoretical results in terms of ultimate load P_{ult} and deflection f_{ult} . (from [12]).	93
Table 4.16	Experimental and theoretical (from [12]).	95
Table 4.17	Mix details for HPC and OPC design with EAF slag referring to 1 m ³ of concrete (from [4]).	98
Table 4.18	Mix details natural aggregates concrete referring to 1 m ³ of concrete (from [4]).	99
Table 4.19	Fresh properties of HPC and OPC concretes with EAF slag (from [4]).	99
Table 4.20	Apparent diffusion coefficients for OPC'and HPC with EAF slag'(from [17]).	104
Table 5.1	Environmental emissions for natural aggregates ($FU = 1$ ton)	124
Table 5.2	Environmental emissions for EAF aggregates ($FU = 1$ ton)	126
Table 5.3	Mix details of the two analyzed concretes.	127
Table 5.4	Mechanical properties of the two analyzed concretes.	128
Table 5.5	Environmental emission related to global and regional scale categories—cement ($FU = 1$ kg).	128
Table 5.6	Total environmental emission related to global and regional scale categories—NA concrete and EAF slag concrete ($FU = 1$ m ³)	128
Table 5.7	Mix details of the two analyzed concretes.	129
Table 5.8	Mechanical properties of the two analyzed concretes.	130
Table 5.9	Total environmental emission related to global and regional scale categories—NA concrete and EAF slag concrete ($FU = 1$ m ³)	130
Table 5.10	Example of inventory data for land use.	136
Table 6.1	Field of applications of the collected works.	142
Table 6.2	Physical properties of EAF slag—database	144
Table 6.3	Chemical composition of EAF slag—database	148
Table 6.4	Chemical composition of EAF slag—database	150
Table 6.5	Leaching potential of EAF slag—database	151
Table 6.6	Concrete mixtures details including EAF slag	153

Contents

1	Introduction	1
1.1	Objectives of the Book.....	1
2	Recycled Aggregates for Concrete Production: State-of-the-Art	5
2.1	Construction and Demolition Waste.....	5
2.1.1	Processing Procedures for Recycled Aggregates Production.....	8
2.1.2	International Codes, Guidelines and Regulations.....	9
2.1.3	RAC Concrete—Mixture Proportioning	15
2.1.4	RAC Concrete—Mechanical Properties.....	17
2.1.5	RAC Concrete—Durability.....	18
2.1.6	RAC Concrete—Structural Concrete.....	19
2.2	Metallurgical Slag.....	20
2.2.1	EAF Slag—Characterization	23
2.2.2	EAF Slag Concrete.....	25
2.3	Fly Ash	27
	References.....	29
3	Workability and Rheology of Fresh Recycled Aggregate Concrete	35
3.1	Introduction	35
3.2	Rheology Background	37
3.2.1	Rheological Models and Flow Curve Equations	37
3.2.2	Bingham Parameters	40
3.2.3	Time-Dependent Behavior.....	42
3.2.4	Stability and Segregation.....	43
3.2.5	Relative Contributions on the Behavior of Fresh Concrete	43
3.2.6	Governing Equations.....	46
3.3	Test Methods for Evaluating Fresh Concrete Properties	47

3.4	Evaluation of Rheological Parameters with Coaxial Cylinders Viscometer	53
3.4.1	Reiner-Riwlin Equation	54
3.4.2	Plug Flow and Gravel Migration Influence	58
3.4.3	Rheographs	61
3.5	Mix Proportion Design of Coarse Recycled Aggregate Concrete and Its Effect on Workability.	61
3.5.1	DVR, DWR and EMV Proportioning Methods	62
3.5.2	Slump Test Results	66
3.5.3	Viscometric Results.	67
3.5.4	Slump—Yield Stress Relation	70
3.6	Conclusions	73
	References.	74
4	Electric Arc Furnace Slag Concrete.	77
4.1	Introduction	77
4.2	EAF Slag Properties	78
4.2.1	Physical Properties	78
4.2.2	Chemical Composition	80
4.3	Ordinary Strength Concrete with EAF Aggregates	82
4.3.1	Fresh Concretes Properties	82
4.3.2	Mechanical Properties	85
4.3.3	Durability-Related Properties.	87
4.3.4	Structural Behavior of RC Beams with EAF Concrete	91
4.4	High Strength Concrete with EAF Aggregates	97
4.4.1	Fresh and Hardened Concrete Properties.	98
4.4.2	Durability-Related Concrete Properties	102
4.5	Conclusions	104
	References.	105
5	Sustainability of Recycled Concretes Through Life Cycle Assessment.	107
5.1	Introduction	107
5.2	Recycled Aggregates and Potential Environmental Issues.	109
5.3	Sustainability Indicators	110
5.3.1	Life Cycle Assessment	111
5.3.2	Abiotic Depletion and Exhaustion Time Indicators	117
5.3.3	Land Use	118
5.4	LCA of Natural and Recycled Aggregates	119
5.4.1	Natural Aggregates	119
5.4.2	Electric Arc Furnace Slag Aggregates.	124
5.5	LCA of Concretes with Recycled Aggregates.	126
5.5.1	Concrete with EAF Slag	127
5.5.2	The Influence of Cement Content on Concrete Emissions	129

- 5.5.3 The Influence of Aggregates Specific Weight
on Concrete Emissions: System Boundary Expansion. . . . 130
 - 5.5.4 The Choice of the Functional Unit 132
- 5.6 Natural Aggregates Depletion at Local Scale 133
- 5.7 Land Use Preservation 135
- 5.8 Conclusions 137
- References. 138
- 6 Experimental Database of EAF Slag Use in Concrete 141**
 - 6.1 Introduction 141
 - 6.2 Physical Properties 141
 - 6.3 Chemical Composition 143
 - 6.4 Mineralogy 143
 - 6.5 Leaching 149
 - 6.6 Application in Concrete as Recycled Aggregate 152
 - 6.7 Conclusion 172
 - References. 173

Chapter 1

Introduction

1.1 Objectives of the Book

The recycling of building materials has relatively ancient origins, since when Romans used construction waste such as ceramics in the so-called opus caementicium, the roman concrete, or when they used crushed slag from the crude iron production for roads building. However, from long time ago, recycling of mineral fraction of demolition wastes and a great part of industrial waste has been not considered as a real, effective alternative of waste disposal. Additionally, for centuries, the construction industry has consumed raw materials, causing also great stream of wastes, which needed to be landfilled. An enormous amount of space was dedicated to the disposal of those materials, leading to the increase of the ecological footprint of construction market.

In the last decades however the research community was pushed to study new fields of application for the wastes coming from construction and demolition operations, driven both by the arise of an environmental consciousness in the society, and also by the realization of the possible depletion of non-renewable natural resources, at least at local scale. From many years also iron and more generally steelmaking slag have been employed as compounds of cement-based materials: for instance the use of ground granulated blast furnace slag in cement manufacture as a partial substitute of Portland cement clinker has become a very well-known practice, currently standardized in EN 197-1. The use of other kinds of slag as artificial aggregates in concrete for civil engineering applications is also commonly diffused.

Accordingly many research works have been developed in the last years, aiming to explore the possibility to substitute, at high percentages, natural aggregates or traditional binders with recycled materials, e.g. recycled aggregates coming from construction and demolition waste (C&DW), metallurgical industry, and supplementary cementing materials. Promising results have been obtained with the production of “green concretes”, which can be potentially ready-applied into the

market, as in the case of concretes including coarse recycled aggregates from C&DW. Their use for structural purposes is also accepted by the current design codes, but generally aggregates origin and the strength class of the structure where they will be placed limit their maximum content. Most of the mechanical and durability properties of recycled aggregate concrete have been widely studied, and currently we are able to properly design this material, for the intended target during structure service life. However few aspects are still not sufficiently explored: this is the case of the workability and rheology of fresh recycled concrete mixtures. Very few data are currently available to predict how this material will flow during casting conditions.

Less research works have been carried out about the use of metallurgical slag use in cement-based materials. Over recent decades the steelmaking industry in Europe has been radically transformed; electric arc furnace technology has largely replaced blast furnaces and Linz-Donawitz converters, leading to the appearance of a new by-product: Electric Arc Furnace (EAF) oxidizing slag. Promising results have been obtained when using this material for producing structural concrete, however still few data exist about its durability and long-term behavior.

Benefits obtained through the use of recycled components in construction materials should be however quantified: often the term “green-concrete” is used, but few proofs of the real embodied energy of the product are given.

The book is structured as follows: Chap. 2 provides the state-of-the-art about the current uses of recycled aggregates, coming from construction and demolition waste and from by-products, in cement-based materials; also supplementary cementing materials are covered by this review. The existing Codes and Guidelines regulating their application for structural concrete in several Countries are described.

Chapter 3 deals with a particular property of recycled aggregate concrete: its workability and rheology in the fresh state. The most diffused experimental methods for evaluating workability, consistency, flowability and passing ability are reviewed. Rheology of fresh cement-based materials, i.e. cement pastes, mortar and fresh concrete, is discussed, particularly with respect to fresh recycled concrete. Some experimental data collected from literature have been used, aiming to highlighting the influence of some design parameters on the overall behavior of the mixtures in the fresh state.

The design of concretes with recycled aggregate coming from metallurgical slag is covered by Chap. 4: some results collected from experimental campaign have been used to assess the influence of aggregates properties on the overall mechanical strength and durability of the concrete. The use of electric arc furnace slag for both replacing coarse and fine aggregates has been discussed.

Chapter 5 analyzes the environmental problems related to the use of recycled materials in concrete. Here a procedure for evaluating the environmental impacts of recycled aggregates and recycled concretes is described. Some examples about how performing a comparative estimation between two different recycled concretes are provided. Additionally some other environmental indicators, useful to capture environmental problems at local and regional scale, are described.

Lastly Chap. 6 provides a database about the available experimental results about electric arc furnace slag characterization and possible application in civil engineering applications. This original database can be used for comparing the properties of different slag, and to assess how they influence the properties of the material where they have been placed.

Chapter 2

Recycled Aggregates for Concrete Production: State-of-the-Art

2.1 Construction and Demolition Waste

All the waste materials coming from construction and demolition operations are known as C&DWs. These materials represent one of the most voluminous stream of waste generated in the world, accounting for about 25–30 % of the whole waste produced in the EU. As an indicative data, approximately 3 billion tons of waste are generated in EU 27 each year. Of this, around one third (1 billion tons) comes from construction and demolition activities [1]. C&DW typically comprises large quantities of inert mineral materials, with smaller amounts of a range of other components, depending on the source and separation techniques. The Waste Framework Directive 2008/98/EC [2] excludes from its definition the uncontaminated soil and other naturally occurring material, which are excavated during construction activities, when the material is used, and remains on site. However C&DW definition and composition may vary from state to state (e.g. with respect to the inclusion of excavated soil), and hence some caution is needed when reviewing statistics about its production in Europe and, more generally speaking, around the world. In the US total C&DW was estimated to be 170 million tons in 2003 [3]: a large fraction of this amount ends up in C&D landfills, and barriers to materials recovery still exist. Several reasons can explain the still low valorization of C&DW, including that buildings are not designed to be nor reused nor recycled, there is a lack of recovery facilities in some areas, and for some materials, the demand is too low due to the unwillingness to use recycled materials in place of virgin ones principally for some regulatory preventions. The competitiveness of C&DW recycling could be improved with several operations, i.e. raising the price of raw materials, through taxation, and setting End-of-Waste criteria for certain C&DW fractions [4].

Concerning C&DW composition, generally it is divided into five main fractions: metal, concrete and mineral, wood, miscellaneous and unsorted mixed fraction. More precisely, it may contain:

- concrete;
- bricks, tiles and ceramics;
- wood;
- glass;
- plastic;
- bituminous mixtures and tars;
- metals (ferrous and non-ferrous);
- soils and stones;
- insulation materials (including asbestos);
- gypsum-based materials (including plasterboards);
- chemicals;
- waste electronic and electrical equipment (WEEE);
- packaging materials;
- hazardous substances.

In this list several hazardous substances appear, which are generally present in building materials because they are used, together with concrete, for completing the structure and for realizing the finishes. These substances are asbestos (found in insulation, roofs and tiles and fire-resistant sealing), lead based paints (found on roofs, tiles and electrical cables), phenols (in resin-based coatings, adhesives and other materials), polychlorinated biphenyls (PCBs) (which can be found in joint sealing and flame-retardant paints/coats, as well as electrical items) and polycyclic aromatic hydrocarbons (PAHs) (frequently present in roofing felt and floorings). The composition of C&DW generally varies highly in relation to the site, because of the local typology and construction technique, climate conditions, economic activities and technologic development of an area, and hence it is difficult to define univocally a composition representative for a large region. The composition of C&DW is also changing during time, due to ageing of the existing buildings and to the low-quality structures, especially build between 1960s and 70s, which are coming to the end of their lifetimes and needing demolishing [5]. Selective demolition of existing structures can determine clear benefits in this context: it would not only reduce the amount of waste destined to landfill, but also increases the quality of the recycled aggregates, minimizing the quantity of impurities and contaminant in the C&DW [6]. However this approach is still under debate, mainly because of the slight practical value and economic benefit, even though some Countries are encouraging this practice [7]. Additionally, in the next future, waste management will be more controlled by the waste treatment BAT reference document (WT BREF) currently under preparation, including when dealing with C&DW management [8].

Concerning C&DW composition, as an indicative data, also inside a single State, it can be very different: for instance in Northern Italy, soils and stone represent the 17 % of the whole waste, but in Central Italy this datum decreases until the 4 % [9]. In average, Italian composition of C&DW is constituted by about 32 % of mixed construction and demolition waste, 27 % of a mixture of concrete, bricks, tiles and