

# Porous Materials


Processing and Applications

## 多孔材料

制备 · 应用 · 表征

[中] P. S. Liu    [中] G. F. Chen

清华大学出版社



# Porous Materials

Processing and Applications

## 多孔材料

制备·应用

潮州表征

潮州表征

潮州表征

藏书章

[中] P. S. Liu [中] G. F. Chen

清华大学出版社  
北京

## 内容简介

多孔材料具有优秀的物理和力学性能,特别是在功能结构一体化方面展示出优异的综合性能。本书系统介绍了此类材料的概念、制备、应用和表征等基本知识以及近年来的相关研究进展。全书共分 10 章:在第 1 章对多孔材料作了整体性的概述,第 2 章至第 8 章依次论述了多孔金属、多孔陶瓷、泡沫塑料三大类多孔材料的各种制备方法和不同用途,第 9 章和第 10 章分别介绍多孔材料的几个基本参量的表征,包括孔隙因素和基本物理性能。本书可供材料领域的科研人员、工程技术人员参考,也可作为高等院校材料类和相关专业(如物理、化学、生物、医学、机械、冶金、建筑等专业)的教材。

版权所有,侵权必究。侵权举报电话:010-62782989 13701121933

### 图书在版编目(CIP)数据

多孔材料:制备·应用·表征=Porous materials: processing and applications: 英文/  
刘培生,陈国锋著.--北京:清华大学出版社,2014

ISBN 978-7-302-38364-2

I. ①多… II. ①刘… ②陈… III. ①多孔性材料—英文 IV. ①TB39

中国版本图书馆 CIP 数据核字(2014)第 247259 号

责任编辑:柳萍

封面设计:何凤霞

责任印制:沈露

出 版 者:清华大学出版社

网 址: <http://www.tup.com.cn>, <http://www.wqbook.com>

地 址:北京清华大学学研大厦 A 座 邮 编:100084

社 总 机:010-62770175

邮 购:010-62786544

投稿与读者服务:010-62776969, [c-service@tup.tsinghua.edu.cn](mailto:c-service@tup.tsinghua.edu.cn)

质量反馈:010-62772015, [zhiliang@tup.tsinghua.edu.cn](mailto:zhiliang@tup.tsinghua.edu.cn)

印 装 者:三河市中晟雅豪印务有限公司

发 行 者:全国新华书店

开 本:160mm×227mm

印 张:36

版 次:2014 年 11 月第 1 版

印 次:2014 年 11 月第 1 次印刷

定 价:198.00 元

---

产品编号:050596-01

## ABOUT THE AUTHORS

Dr. P. S. Liu is professor at the College of Nuclear Science and Technology, Beijing Normal University (BNU), Beijing, China. He graduated from the Chinese Academy of Science in 1998 and received his Ph.D. in materials science and engineering. He has served as the committeeman of the academic committee of the Key Laboratory of Beam Technology and Material Modification of Ministry of Education of China. Additionally, he was the first director of the Material Physics division and then the vice director of the Nuclear Physics Research Institute at BNU from 2004 to 2008. Investigating porous materials and high-temperature coatings for many years, he has published extensively in the area of materials science and engineering as the lead author, including about 60 SCI papers, more than 50 EI articles, and six academic books. In addition, he has authorized nine Chinese invention patents as the principal originator.

Dr. G. F. Chen, Ph.D. from the Institute of Metal Research, Chinese Academy of Sciences; Alexander von Humboldt Fellow in the Max-Planck-Institute for Metals Research in Stuttgart; research scientist at the National Physical Laboratory in London; research specialist at Cleveland State University in Cleveland, Ohio, professor at the Northwestern Polytechnical University in Xi'an, China, and now an expert in corporate technology at Siemens Ltd., China, in Beijing. He has more than 20 years of experience in materials research and development, particularly with energy materials.

## PREFACE

Porous materials are a class of functional-structural materials with the optimal index of physical and mechanical properties, thanks to their porous structure. This book systematically introduces the basic concept behind these materials, as well as their major types, characteristics, applications, and main parameters. In addition, it presents various methods that can be used to process porous metals, porous ceramics, and polymer foams (foamed plastics) in accordance with their respective categories.

The concept of porous materials has been known for a number of years, but its radiation is far less successful than that of other materials. By the end of the 20th century, studies on porous materials have made a number of important discoveries. Based on this background, we spent a good deal of time and energy on collecting relevant literatures, combining with our own accumulated work experience, to write the Chinese version of the book, *Introduction to Porous Materials*, published in 2004 by Tsinghua University Press. This book focuses on production methods and applications of porous materials, considering that a classic work about porous materials, *Cellular Solids: Structure and Properties*,<sup>1</sup> by L. J. Gibson and M. F. Ashby, has made a great contribution to expounding the structure and properties of porous solids. This is aimed at providing more information to scientific researchers and engineering or technical personnel who interact with porous materials (including the present authors themselves, of course). The formation and the publication of *Introduction to Porous Materials* were quite hasty at that time, with some immature viewpoints. In addition, at that time, there were only a few researchers in China studying porous materials. However, the results of our previous effort (including its reception) far exceeded our expectations, and that development further encouraged our future work. In turn, the publication of this book may play a part in promoting the development in China of the porous material field, as well as research in relevant or potential relevant fields. Because we have seen that research into porous materials has been growing rapidly in recent years in China, and the number of the scientific research institutes, universities, and companies involved in this area also have increased rapidly.

In order not to let down the readers, the publisher and the author jointly determined to revise the original book for a second edition, published in

Chinese, to better meet the needs of the wider readership. In the second edition published in 2012, we corrected some errors and inappropriate content that appeared in the first edition, and we added relevant new content reflecting the research progress made over the previous decade. In addition, we readjusted the layout of the book to give it a scientific and reasonable arrangement; in particular, we devoted a lot of time to revising chapters 2, 3, and 4.

Learning of Elsevier's interest in the topic of this book and considering the international demand for it, we comprehensively rewrote and rearranged the book again for a third edition. In so doing, we expanded on the relevant contents with an emphasis on supplementing the information about the processing, applications, and characterization of porous materials.

In the process of writing this book, we referred to the relevant papers and works published in the last 40 years, and especially those from the last 20 years, and made good use of them. Here, we would like to express our heartfelt thanks to all the authors of these documents. However, we should note that due to space and time limitations, we had to leave out a good many worthy books, papers, and articles, and we regret this deeply. Certainly, we also should acknowledge the assistance of many of our colleagues in the field of porous materials, and our friends that have helped and supported us greatly. In the process of writing and publishing this book, P. Liu provided excellent assistance, and C. Y. Yang and Y. J. Guo worked hard to collate the references and draw the figures for this book. The combined effort of all these fine people have allowed this project to reach a successful conclusion.

P.S. Liu, G.F. Chen

October 2013

# CONTENTS

*About the Author*

*ix*

*Preface*

*xi*

|  |           |
|--|-----------|
| <b>1. General Introduction to Porous Materials</b> | <b>1</b>  |
| 1.1 Elementary Concepts for Porous Materials       | 1         |
| 1.2 Main Groups of Porous Materials                | 2         |
| 1.3 Porous Metals                                  | 6         |
| 1.3.1 Powder-sintering type                        | 6         |
| 1.3.2 Fiber-sintering type                         | 8         |
| 1.3.3 Melt-casting type                            | 8         |
| 1.3.4 Metal-deposition type                        | 9         |
| 1.3.5 Directional-solidification type              | 10        |
| 1.3.6 Composite type                               | 10        |
| 1.4 Porous Ceramics                                | 11        |
| 1.4.1 Classifying porous ceramics                  | 12        |
| 1.4.2 Characteristics of porous ceramics           | 14        |
| 1.5 Polymer Foams                                  | 15        |
| 1.5.1 Classifying polymer foams                    | 15        |
| 1.5.2 Characteristics of polymer foams             | 17        |
| 1.6 Conclusions                                    | 19        |
| References   | 19        |
| <b>2. Making Porous Metals</b>                     | <b>21</b> |
| 2.1 Powder Metallurgy                              | 21        |
| 2.1.1 Preparation of metal powders                 | 22        |
| 2.1.2 Molding of the porous body                   | 28        |
| 2.1.3 Sintering of the porous body                 | 34        |
| 2.2 Fiber Sintering                                | 50        |
| 2.2.1 Preparation of metal fibers                  | 51        |
| 2.2.2 Preparation of porous bodies                 | 53        |
| 2.2.3 Electrode plate with porous metal fibers     | 55        |
| 2.3 Metallic Melt Foaming                          | 57        |
| 2.3.1 Preparation of porous bodies                 | 57        |
| 2.3.2 Technical problems and solutions             | 58        |
| 2.3.3 Case studies on porous aluminum preparation  | 60        |
| 2.4 Gas Injection into the Metallic Melt           | 61        |
| 2.5 Infiltration Casting                           | 65        |

|       |  |     |
|-------|--|-----|
| 2.6   | Metal Deposition                                   | 69  |
| 2.6.1 | Vapor deposition                                   | 69  |
| 2.6.2 | Electrodeposition                                  | 73  |
| 2.6.3 | Reaction deposition                                | 83  |
| 2.7   | Hollow Ball Sintering                              | 83  |
| 2.7.1 | Preparation of hollow balls                        | 84  |
| 2.7.2 | Preparation of porous bodies                       | 85  |
| 2.7.3 | Fe-Cr alloy porous products                        | 86  |
| 2.8   | Preparation of the Directional Porous Metal        | 86  |
| 2.8.1 | Solid-gas eutectic solidification                  | 86  |
| 2.8.2 | Directional solidification                         | 89  |
| 2.9   | Other Methods                                      | 92  |
| 2.9.1 | Powder melting foaming                             | 92  |
| 2.9.2 | Investment casting                                 | 95  |
| 2.9.3 | Self-propagating, high-temperature synthesis (SHS) | 96  |
| 2.10  | Preparation of Porous Metal Composites             | 99  |
| 2.11  | Special Processing of Porous Metals                | 104 |
| 2.12  | Concluding Remarks                                 | 107 |
|       | References   | 108 |

### **3. Application of Porous Metals** **113**

|       |   |     |
|-------|---|-----|
| 3.1   | Introduction  | 113 |
| 3.1.1 | Functional applications                                   | 113 |
| 3.1.2 | Structural applications                                   | 114 |
| 3.2   | Filtration and Separation                                 | 115 |
| 3.2.1 | Industrial filtration                                     | 116 |
| 3.2.2 | Gas purification  | 116 |
| 3.3   | Sound Absorption  | 120 |
| 3.3.1 | Sound absorption mechanism of metal foams                 | 121 |
| 3.3.2 | Influence factor of sound absorption                      | 123 |
| 3.3.3 | Metal foam with improved sound absorption                 | 126 |
| 3.3.4 | Applications  | 128 |
| 3.3.5 | The model for calculation of sound absorption coefficient | 130 |
| 3.4   | Heat Exchange   | 133 |
| 3.4.1 | Heat exchanger  | 134 |
| 3.4.2 | Heat radiator   | 135 |
| 3.4.3 | Heat tube   | 136 |
| 3.4.4 | Resistance heater   | 137 |
| 3.4.5 | Composite phase transformation materials                  | 139 |
| 3.4.6 | Cooling materials   | 141 |



|           |   |            |
|-----------|---|------------|
| 3.5       | Porous Electrode  | 141        |
| 3.5.1     | Nickel foam   | 143        |
| 3.5.2     | Pb foam   | 143        |
| 3.5.3     | Fuel cell   | 145        |
| 3.6       | Application in Transportation                                       | 146        |
| 3.6.1     | Light structure   | 147        |
| 3.6.2     | Absorption of impact energy   | 148        |
| 3.6.3     | Noise control   | 148        |
| 3.6.4     | Other options   | 149        |
| 3.7       | Applications in Biology and Iatrology                               | 151        |
| 3.7.1     | Applicability of materials  | 151        |
| 3.7.2     | Mechanical requirements   | 153        |
| 3.7.3     | Ti foam   | 154        |
| 3.7.4     | Ta and stainless steel foams  | 157        |
| 3.7.5     | Gradient structure and composite                                    | 159        |
| 3.7.6     | Mechanism of bone formation   | 160        |
| 3.8       | Other Applications  | 162        |
| 3.8.1     | Energy absorption and vibration control                             | 162        |
| 3.8.2     | Electromagnetic shielding   | 166        |
| 3.8.3     | Fighting flames   | 167        |
| 3.8.4     | Mechanical parts  | 168        |
| 3.8.5     | Building materials  | 171        |
| 3.8.6     | Catalytic reactions   | 172        |
| 3.9       | Some Application Illustrations for Refractory Metal Porous Products | 176        |
| 3.9.1     | W foam  | 176        |
| 3.9.2     | Ta foam   | 178        |
| 3.9.3     | Mo foam   | 179        |
| 3.10      | Concluding Remarks  | 181        |
|           | References  | 182        |
| <b>4.</b> | <b>Special Porous Metals</b>  | <b>189</b> |
| 4.1       | Amorphous Metal Foams (AMFs)  | 189        |
| 4.2       | Gradient Porous Metals  | 193        |
| 4.3       | Porous Metallic Lattice Materials                                   | 198        |
| 4.4       | Nanoporous Metal Foams (NMFs)                                       | 203        |
| 4.5       | Porous Metallic Films and Thin Films Carried on Metal Foams         | 215        |
| 4.5.1     | Porous metallic films   | 215        |
| 4.5.2     | Thin films carried on metal foam                                    | 216        |
| 4.6       | Conclusions   | 218        |
|           | References  | 219        |

|   |            |
|---|------------|
| <b>5. Fabricating Porous Ceramics</b>                       | <b>221</b> |
| 5.1 Particle Stacking Sintering                             | 222        |
| 5.2 Appending Pore-forming Agent                            | 223        |
| 5.2.1 Addition of pore-forming material in powders          | 223        |
| 5.2.2 Slurry with pore-forming agent                        | 228        |
| 5.3 Polymeric Sponge Impregnation Process                   | 233        |
| 5.3.1 The selection of organic foam and the pretreatment    | 234        |
| 5.3.2 Ceramic slurry preparation and impregnating           | 234        |
| 5.3.3 Drying and sintering of green bodies                  | 238        |
| 5.3.4 Progress of organic foam impregnating in slurry       | 239        |
| 5.3.5 The obtainment of the ceramic foam with high strength | 241        |
| 5.4 Foaming Process   | 244        |
| 5.4.1 Green body foaming                                    | 244        |
| 5.4.2 Slurry foaming  | 246        |
| 5.4.3 Evaluation of the processing                          | 253        |
| 5.5 Sol-gel Method  | 255        |
| 5.5.1 Different templates                                   | 255        |
| 5.5.2 Example of preparation of porous ceramics             | 256        |
| 5.6 New Processing of Porous Ceramics                       | 258        |
| 5.6.1 Gel casting   | 258        |
| 5.6.2 Wood ceramics   | 262        |
| 5.6.3 Freeze-drying method                                  | 264        |
| 5.6.4 Self-propagating high-temperature synthesis (SHS)     | 265        |
| 5.6.5 Hollow-sphere sintering                               | 266        |
| 5.6.6 Other processes                                       | 268        |
| 5.7 The Preparation of New Types of Porous Ceramic          | 270        |
| 5.7.1 Hydrophobic porous ceramics                           | 270        |
| 5.7.2 Ceramic foam with gradient pores                      | 271        |
| 5.7.3 Fiber-porous ceramics                                 | 274        |
| 5.7.4 Slender porous ceramic tubes                          | 275        |
| 5.7.5 Porous ceramics with directionally arrayed pores      | 277        |
| 5.7.6 Porous ceramic powder                                 | 277        |
| 5.8 Preparation of Porous Ceramic Membranes                 | 278        |
| 5.8.1 Sol-gel   | 279        |
| 5.8.2 Other methods   | 280        |
| 5.8.3 Preparation examples for porous ceramic membranes     | 281        |
| 5.8.4 A porous $\text{TiO}_2$ film with submicropores       | 283        |
| 5.9 Porous Ceramic Composites                               | 292        |
| 5.10 Ceramic Honeycombs                                     | 295        |
| 5.11 Concluding Remarks                                     | 296        |
| References  | 296        |

|  |            |
|--|------------|
| <b>6. Applications of Porous Ceramics</b>                  | <b>303</b> |
| 6.1 Filtration and Separation                              | 303        |
| 6.1.1 Filtration of molten metals                          | 304        |
| 6.1.2 Hot gas filtration                                   | 310        |
| 6.1.3 Microfiltration                                      | 311        |
| 6.1.4 Fluid separation                                     | 312        |
| 6.1.5 Parameters of separation and filtration              | 315        |
| 6.2 Functional Materials                                   | 316        |
| 6.2.1 Biological materials                                 | 316        |
| 6.2.2 Ecomaterials (Environmental materials)               | 319        |
| 6.2.3 Heat insulation and exchange                         | 321        |
| 6.2.4 Sound absorption and damping                         | 322        |
| 6.2.5 Sensors (sensing elements)                           | 330        |
| 6.3 Chemical Engineering                                   | 331        |
| 6.3.1 Catalyst carriers                                    | 331        |
| 6.3.2 Porous electrodes and membranes                      | 333        |
| 6.3.3 Ion exchange and desiccants                          | 337        |
| 6.3.4 Gas introduction                                     | 337        |
| 6.4 Combustion and Fire Retardance                         | 338        |
| 6.4.1 Combustor  | 338        |
| 6.4.2 Flame arrester                                       | 339        |
| 6.5 Overall Comments on the Application of Porous Ceramics | 339        |
| 6.6 Concluding Remarks                                     | 341        |
| References   | 342        |
| <b>7. Producing Polymer Foams</b>                          | <b>345</b> |
| 7.1 The Foaming Mechanism of Plastic Foam                  | 345        |
| 7.1.1 Raw materials  | 345        |
| 7.1.2 Foaming methods                                      | 352        |
| 7.1.3 Formation of bubble nuclei                           | 354        |
| 7.1.4 Growth of bubbles                                    | 355        |
| 7.1.5 Stabilization and solidification of the foamed body  | 357        |
| 7.1.6 The foaming of some plastics                         | 360        |
| 7.2 Molding Process for Polymer Foams                      | 361        |
| 7.2.1 Extrusion foaming                                    | 361        |
| 7.2.2 Injection molding                                    | 362        |
| 7.2.3 Pour foaming   | 363        |
| 7.2.4 Mold pressing  | 364        |
| 7.2.5 Reaction injection molding (RIM)                     | 364        |
| 7.2.6 Rotation foaming                                     | 366        |
| 7.2.7 Hollow blowing                                       | 366        |
| 7.2.8 Microwave sintering                                  | 367        |

|       |   |     |
|-------|---|-----|
| 7.3   | Flame-Retardant Polymer Foam                | 367 |
| 7.3.1 | Anti-flaming                                | 368 |
| 7.3.2 | Common flame-retarding plastic foams        | 369 |
| 7.4   | Progress of Plastic Foam Preparation        | 371 |
| 7.4.1 | Modification of traditional foamed plastics | 372 |
| 7.4.2 | Microcellular plastics                      | 373 |
| 7.4.3 | Sound-absorbing plastic foams               | 374 |
| 7.4.4 | Biodegradable foamed plastics               | 374 |
| 7.4.5 | Reinforced foamed plastic                   | 375 |
| 7.4.6 | Posttreatment of foamed plastics            | 375 |
| 7.4.7 | Plant oil-based plastic foams               | 376 |
| 7.4.8 | PU plastic foam                             | 377 |
| 7.5   | Concluding Remarks                          | 378 |
|       | References                                  | 379 |

## **8. Applications of Polymer Foams 383**

|       |   |     |
|-------|---|-----|
| 8.1   | Thermal Insulation Materials  | 383 |
| 8.1.1 | Factors affecting thermal insulation performance                                | 384 |
| 8.1.2 | Thermal insulation and energy saving construction                               | 384 |
| 8.2   | Packaging Materials   | 385 |
| 8.3   | Sound-Absorbing Materials   | 387 |
| 8.3.1 | Product features  | 387 |
| 8.3.2 | Sound absorption principles and mechanisms                                      | 388 |
| 8.3.3 | PU foam   | 389 |
| 8.4   | Separation and Enrichment   | 389 |
| 8.4.1 | Working principles  | 390 |
| 8.4.2 | Modification application  | 391 |
| 8.4.3 | Enrichment of organic poisonous matters   | 393 |
| 8.5   | Other Applications  | 393 |
| 8.5.1 | Dust arrestment   | 393 |
| 8.5.2 | Structural materials  | 394 |
| 8.5.3 | Fireproofing technology and active explosion suppression                        | 395 |
| 8.5.4 | Buoyancy  | 396 |
| 8.6   | Applications of Typical Kinds of Polymer Foam                                   | 396 |
| 8.6.1 | Thermosetting polymer foams   | 397 |
| 8.6.2 | Thermoplastic general polymer foams   | 399 |
| 8.6.3 | Engineering thermoplastic foams   | 401 |
| 8.6.4 | High-temperature-resistant polymer foams (using temperatures higher than 200°C) | 402 |
| 8.6.5 | Functional polymer foams  | 402 |
| 8.6.6 | Other polymer foams   | 403 |

|   |     |
|---|-----|
| 8.7 New, Functional Polymer Foams               | 404 |
| 8.7.1 Microcellular plastics                    | 404 |
| 8.7.2 Magnetic polymer foams                    | 405 |
| 8.7.3 Porous, self-lubricating plastics         | 406 |
| 8.8 Overall Application Review of Polymer Foams | 407 |
| 8.9 Conclusions                                 | 407 |
| References                                      | 408 |

## **9. Characterization Methods: Basic Factors** **411**

|   |     |
|---|-----|
| 9.1 Porosity  | 411 |
| 9.1.1 Basic mathematical relationship               | 412 |
| 9.1.2 Microscopic analysis                          | 412 |
| 9.1.3 Mass-volume direct calculation                | 413 |
| 9.1.4 Soaking medium                                | 414 |
| 9.1.5 Vacuum dipping                                | 416 |
| 9.1.6 Floating                                      | 417 |
| 9.2 Pore Size                                       | 419 |
| 9.2.1 Microscopic analysis                          | 420 |
| 9.2.2 Bubble method                                 | 420 |
| 9.2.3 Penetrant method                              | 432 |
| 9.2.4 Gas permeation                                | 433 |
| 9.2.5 Liquid-liquid method                          | 437 |
| 9.2.6 Gas adsorption                                | 442 |
| 9.3 Pore Morphology                                 | 447 |
| 9.3.1 Microobservation method                       | 447 |
| 9.3.2 X-Ray tomography                              | 448 |
| 9.3.3 Potential examination by DC of pore defects   | 460 |
| 9.3.4 Other methods                                 | 463 |
| 9.4 Specific Surface Area                           | 464 |
| 9.4.1 Gas adsorption method (BET method)            | 464 |
| 9.4.2 Fluid penetrant method                        | 473 |
| 9.5 Mercury Intrusion Method                        | 475 |
| 9.5.1 Principle of mercury intrusion                | 476 |
| 9.5.2 Measurement of pore size and distribution     | 477 |
| 9.5.3 Measurement of specific surface area          | 479 |
| 9.5.4 Measurement of apparent density and porosity  | 480 |
| 9.5.5 Experimental instrument for mercury intrusion | 483 |
| 9.5.6 Measurement error analysis and treatment      | 483 |
| 9.5.7 Scope of application                          | 487 |
| 9.5.8 Comparison of the different methods           | 488 |
| 9.6 Concluding Remarks                              | 489 |
| References  | 490 |

|   |                |
|---|----------------|
| <b>10. Characterization Methods: Physical Properties</b>        | <b>493</b>     |
| 10.1 Sound Absorption Coefficient                               | 493            |
| 10.1.1 Characterization of sound absorbability                  | 494            |
| 10.1.2 Measurement of the sound absorption coefficient          | 495            |
| 10.1.3 Analysis and discussion                                  | 505            |
| 10.2 Thermal Conductivity                                       | 507            |
| 10.2.1 Characterization of thermal conductivity and diffusivity | 507            |
| 10.2.2 Measurement of thermal conductivity                      | 509            |
| 10.2.3 Measurement of thermal conductivity for porous materials | 514            |
| 10.2.4 Evaluation of performance                                | 521            |
| 10.3 Electrical resistivity/Electrical Conductivity             | 523            |
| 10.3.1 Four-probe method  | 523            |
| 10.3.2 Double bridge method                                     | 524            |
| 10.3.3 Potentiometer method                                     | 528            |
| 10.3.4 Eddy method  | 529            |
| 10.4 Concluding Remarks   | 531            |
| References  | 532            |
| <br><i>Index</i>  | <br><b>533</b> |

# General Introduction to Porous Materials

Porous materials widely exist around us and play a role in many aspects of our daily lives; among the fields they can be found in are energy management, vibration suppression, heat insulation, sound absorption, and fluid filtration. Highly porous solids have relatively high structural rigidity and low density of mass, so porous solids often serve as structural bodies in nature, including in wood and bones [1,2]; but human beings use porous materials more functionally than structurally, and develop many structural and functional integrative applications that use these materials fully [3,4]. This chapter will introduce the elementary concepts and features of this kind of material.




## 1.1 ELEMENTARY CONCEPTS FOR POROUS MATERIALS

Just as their name implies, porous materials contain many pores. Porous solids are made of a continuously solid phase that forms the basic porous frame and a fluid phase that forms the pores in the solid. The latter can consist of gas, when there is a gaseous medium in the pore, or of liquid, when there is a liquid medium in the pore.

In that case, can all materials with pores be referred to as porous? Perhaps surprisingly, the answer is “no.” For instance, holes and crannies that are the result of defects will lower a material’s performance. This result is not what designers want, and so these materials cannot be termed porous. So-called porous materials must possess two essential characteristics: one is that the material contains a lot of pores, and the other is that the pores are designed specifically to achieve the expectant index of the material’s performance. Thus, the pore of porous materials may be thought as a functional phase what designers and users hope to come forth within the material, and it supplies an optimizing action for the performance of the material.


## 1.2 MAIN GROUPS OF POROUS MATERIALS

The number of pores (i.e., porosity) will vary for different porous materials. Porous materials can be classified as low porosity, middle porosity, or high porosity based on the number of pores. Generally, porous materials with low and middle porosity have closed pores (Figure 1.1) which behave like a phase of impurity. For porous materials with high porosity (Figures 1.2–1.4), there are two different cases according to various morphologies of the pore and the continuous solid phase. In the first case, the continuous solid constructs a two-dimensional array of polygons; the pore is isolated in space, taking on polygonal columniations accordingly; and the cross-sectional shape of the pore is commonly triangle, quadrangle, or hexagon (Figure 1.2). This structure looks similar to the hexagonal cell of a honeycomb, and such two-dimensional porous materials are called *honeycomb materials*. Porous materials with directional pores [5], which are called *lotus-type porous materials*, have a similar structure as honeycomb materials, but the cross-sectional shape of the pores for these materials is circular or elliptic, and the pore often cannot run through it, resulting in less uniformity of distribution and a lower density of the array. In the second case, the continuous solid presents a three-dimensional reticulated structure (Figure 1.3), and such porous materials can be termed *three-dimensional reticulated foamed*




**Figure 1.1** Porous composite oxide ceramics, which is a low-porosity material, shown as a cross-sectional image.






**Figure 1.2** Two-dimensional honeycomb materials: (a) conductive honeycomb TiC ceramics with quasi-square pores [6]; (b) thermal storage of honeycomb ceramics with square pores (with dimensions of 100 mm × 100 mm × 100 mm, cell-wall thickness of 1 mm, and square-pore side length of 2.5 mm) [7].



**Figure 1.3** Three-dimensional reticulated foamed materials: (a) nickel foam; (b) iron foam.



**Figure 1.4** Bubblelike foamed materials: (a) a closed-cell bubblelike foamed material of aluminum foam [8]; (b) an open-cell bubblelike foamed material of iron foam.