

MATERIALS SCIENCE MONOGRAPHS, 42A

MATERIALS DATA FOR CYCLIC LOADING

PART A: UNALLOYED STEELS

CHR. BOLLER

T. SEEGER

MATERIALS SCIENCE MONOGRAPHS, 42A

MATERIALS DATA FOR CYCLIC LOADING

PART A: UNALLOYED STEELS

CHR. BOLLER

Battelle-Institut e.V. Frankfurt/M., F.R.G.

T. SEEGER

Fachgebiet Werkstoffmechanik, Technische Hochschule Darmstadt, F.R.G.



ELSEVIER

Amsterdam — Oxford — New York — Tokyo

1987

SBD/4/01

Preface

Materials data for cyclic loading are becoming increasingly important as a tool for materials characterization and engineering design. They can serve as the basis for a comparative judgement of a material's mechanical behaviour. Furthermore, knowledge of the stress-strain behaviour during cyclic loading is required more and more frequently in finite element calculations of cyclically loaded structural parts. Finally, such data are a fundamental input for the fatigue life estimation procedure known as the Local Strain Approach or Notch Strain Approach. In this procedure, based on fundamental work by Manson, Coffin and Morrow, the local stress-strain path for the elastic plastic behaviour in a notch root is calculated. From a strain life curve the damage contribution of each load cycle can be evaluated and accumulated according to a damage accumulation rule (e.g. that of Palmgren-Miner).

The Local Strain Approach was initially applied only for the estimation of low cycle fatigue lives. This led to early implementation of that procedure in the ASME-Code. In the past few years, the procedure has been generalized to include the estimation of high cycle and random loading fatigue life.

In this handbook only a very rough presentation of the Local Strain Approach is given in the Introduction, perhaps too short for someone not already acquainted with it. For more detailed information the reader should consult the relevant literature. We intend to publish in the future a guide to the capabilities and application of Local Strain Approach, to complete the large number of data presented here.

Materials data for cyclic loading are now evaluated all over the world on un-notched specimens, by measuring stresses, strains and fatigue life. This combination of parameters, which differs from the traditional method by presenting materials fatigue behaviour under cyclic loading only in stress life curves, led us to the idea of collecting such data and evaluating and presenting the characteristic stress-strain and life curves in a unified way.

The initial concept of this compendium was discussed in a working group of "Arbeitskreis Betriebsfestigkeit" of the German Society of Materials Testing (DVM). The work was financed by the German Research Council (DFG) and sponsored by various industrial companies. The aim of this handbook is to make the collected data available to a large number of users. The reason why the experimental results are reported in all their details (stresses, strains, fatigue life) is so that users may judge for themselves how representative the constants evaluated for the stress-strain and strain life curves are. Furthermore, this enables the reader to compose datasets according to his own individu-

al needs and to evaluate the stress-strain and life curves according to equations other than those presented here. This latter possibility should also inspire researchers to deal with the influence of mean stresses, multi-axiality, sequence, size, surface and environmental effects in fatigue life estimation.

The data collection contains about 600 datasets with over 4000 experimental results in total. The majority of data have been taken from the literature. Quite often the experimental values had to be measured from plots as they had not been reported numerically. In this context we have to thank Mrs. I. Pilz for her reliable coordinative work with regard to data processing, computer handling and datasheet output. Our thanks are also due to Mrs. I. Rettig and G. Templin for carrying out the tiresome work of measuring the experimental values from plots in the literature.

With such a large amount of data involved, some mistakes may have remained undetected despite careful proof-reading. Therefore the authors and publishers can accept no responsibility for data that are subsequently found to have been erroneously recorded or inaccurately derived. They would nonetheless be glad to hear from anyone who finds a mistake.

Anyone interested in obtaining access to the computer database should contact the authors.

As materials data for cyclic loading are constantly being evaluated and published, the collection of such data is still going on. We call upon all researchers and scientists working in this field to contribute their published data to this data pool. We would also like to suggest that they test more specimens in low cycle fatigue as well as in the region of the endurance limit. The stress-strain and life curves could then be regarded as really complete.

Darmstadt, May 1987

Chr. Boller
Battelle-Institut e.V.
Frankfurt/M.

T. Seeger
Fachgebiet Werkstoffmechanik
Technische Hochschule Darmstadt

Contents

	page
Introduction.....	1
Nomenclature.....	7
Literature (data sources).....	9
Data sheets:	
α -Fe.....	12
Armco.....	15
St 37.....	19
St 42.....	30
St 42 flame cut.....	34
MSt 42.....	38
MSt 42 elevated temperature.....	41
TSt 42.....	44
TSt 42 elevated temperature.....	47
St 44.....	50
St 46 (SB 46).....	56
St 46 (SB 46) elevated temperature.....	68
St 49 (SB 49).....	104
St 49 (SB 49) elevated temperature.....	107
St 50.....	137
St 52.....	158
H II.....	184
H IIA elevated temperature.....	190
Ck C1.....	193
C 10 (SAE 950 XK).....	196
Ck 10.....	199
Ck 15.....	208
Ck 15 coldformed.....	214
Ck 15 rolled surface.....	226
Ck 15 nitrided surface.....	229
C 20 (A 36).....	232

X

Ck 22.....	233
Ck 25 (S25C).....	250
Ck 27 (AISI 4027) carburized.....	259
Ck 35 (S35C).....	262
Ck 45.....	286
Ck 45 $s_{\text{H}} \neq 0$	329
Ck 45 (SAE-1045) under environmental conditions.....	333
Ck 45 rolled surface.....	341
Ck 45 nitrided surface.....	344
C 60 (12060).....	347
Ck 70.....	353
Ck 80.....	356
Ck 100.....	359
Ck 125 (AISI 40126).....	368

Introduction

Metal Fatigue has traditionally been related to stress. Since the works of Manson [1.1] and Coffin [1.2], however, it has become clear that as well as stress, strains must be taken into account too. If this is done, then we can get a fairly adequate picture of a material's fatigue behaviour. The reason for this is that in fatigue there is usually an elastic-plastic correlation between stresses and strains, quite often in the region of the endurance limit. Therefore the traditional stress-strain curves for monotonic loading are completed by the stress-strain curves for cyclic loading and the traditional stress life curves by the strain life curves for elastic, plastic and total strains. Mean stress effects are described by so-called mean stress (damage) parameter life curves.

Stress-strain curves, strain life curves and mean stress parameter life curves for cyclic loading are the components of "materials data for cyclic loading".

These materials data provide the basis for materials assessment by direct comparison of data or characteristic values and for estimating the crack initiation lives of structural parts under constant and variable amplitude loading.

In the latter case, local stress-strain paths are evaluated by applying a load notch relationship from finite element calculations or from approximation formulas such as Neuber's rule $\sigma_e = K_t^2 \cdot S \cdot e$ (K_t = stress concentration factor, S = nominal stress, e = nominal strain, mainly $e = S/E$), and the stress-strain curve for cyclic loading of the material being studied. With the help of the material's life curve - and in the case of random loading taking damage accumulation into account - the crack initiation lives of structural parts can be calculated. To achieve satisfactory accuracy with this evaluation method, called the Local Strain or Notch Strain Approach, it must be assumed that the conditions of the unnotched specimen for which the materials data have been determined agree sufficiently with the local notch conditions of a structural part regarding the definition of crack initiation, surface roughness or finish and the size of the highly stressed material volume.

The advantage of this method is a great reduction in the cost of evaluating experimental data. Regarding strengths, the multitude of notch effects are eliminated and transferred to the calculation of local stresses and strains. Of course, the accuracy of the life estimation depends on the accuracy of the local stresses and strains calculated, the transferability

of the materials data used and the validity of the damage accumulation rule applied.

For many years now materials data for cyclic loading have been published in the scientific literature. However, these data have been collected in quite different ways. In this book, these materials data have been gathered together, evaluated according to uniform approach and methods and compiled on standardized data sheets.

In gathering the data, special attention was given to ensuring that as far as possible the shape of the specimens and the experimental procedure conformed to ASTM E 606-80 [1.3]. ASTM E 606 is recommended for further evaluation of data on cyclic loaded materials.

The data are now published for the first time in a handbook, suitable for a wide range of applications and divided into the following sections according to material groups:

Part A: Unalloyed Steels

Part B: Low-Alloy Steels

Part C: High-Alloy Steels

Part D: Aluminium and Titanium Alloys

Part E: Cast and Welded Metals

Each data sheet takes up a maximum of four pages. The first page gives a description of the material and testing procedure. In the upper left corner the material designation is given in the following order:

- designation according to DIN 17 006 or DIN 1725
- designation according to DIN 17 007
- usual commercial designation (e.g. ASTM, SAE, JIS)

The chemical composition is always given in weight percent. It corresponds to the value given in the literature referred to.

The second and third pages show the diagrams for

- stress-strain curves for monotonic and cyclic loading
- strain life curve

- mean stress (damage) parameter life curve according to the parameter of Smith, Watson and Topper [1.4].

Unless indicated otherwise in the plots, the experiments were carried out at room temperature in laboratory air.

The diagrams for the stress-strain relationships contain at the most three curves, one for monotonic and two for cyclic loading, the latter being evaluated from incremental step tests and constant amplitude tests. All three curves can be described approximately by an analytical function, for monotonic loading by the equation

$$\epsilon = \epsilon_e + \epsilon_p = \frac{\sigma}{E} + \left(\frac{\sigma}{K}\right)^{1/n} \quad (1a)$$

and for cyclic loading by the equation

$$\epsilon_a = \epsilon_{a,e} + \epsilon_{a,p} = \frac{\sigma_a}{E} + \left(\frac{\sigma_a}{K'}\right)^{1/n'} \quad (1b)$$

The values of the constants K , n and K' , n' are given in the data sheets. They were evaluated by regression analysis (minimum of the squares of the distances rectangular to the regression line) from the values of the appropriate experimental data in the literature referred to. For unalloyed and low-alloy steels the analytical description of the stress-strain curve for monotonic loading according to eq. (1a) is sometimes only meaningful for strains beyond 2%, because yield strength and Lüder's area cannot be accounted for in that equation. The stress-strain curves for cyclic loading were determined on the basis of constant amplitude and/or incremental step test data. Unless noted otherwise in the data sheet, the results are valid for a stabilized state or half fatigue life, respectively. The stress-strain curves obtained from constant amplitude tests are represented by a solid line in the experimentally proved part and by a dashed line in the remaining part. Their constants K' and n' are denoted once more in the diagrams. The stress-strain curves obtained from incremental step tests are drawn up to the maximum strain amplitude tested. Irrespective of the number of curves drawn in the diagram, the legend always contains the symbols for all three curves.

The analytical description for the strain life curves corresponds to the functions of Manson [1.5] and Morrow [1.6]:

$$\epsilon_{a,e}(N) = \frac{\sigma_f'}{E} \cdot (2N)^b \quad (2)$$

$$\epsilon_{a,p}(N) = \epsilon_f' \cdot (2N)^c \quad (3)$$

$$\epsilon_a(N) = \epsilon_{a,e}(N) + \epsilon_{a,p}(N) \quad (4)$$

The number of cycles N characterizes crack initiation or rupture of the specimen according to its loading conditions.

For datasets with no runouts, or only a few, the constants σ_f' , b , ϵ_f' and c were evaluated on the basis of experimental σ_a - ϵ_a - N data from the literature by the aforementioned regression analysis for elastic strains and plastic strains separately. If only a few runouts were available, they were neglected as they give no reliable information about the endurance limit. There is no significant difference between these evaluations of the constants and those obtained according to ASTM E 739-80 [1.7], even though the types of regression analysis are slightly different.

For some data sets with a large number of experimental results in the region of the endurance limit, the constants were evaluated by maximum likelihood method. This was again done separately for elastic and plastic strain according to a proposal made in [1.8] for the evaluation of S-N-curves. The endurance limits obtained are denoted by horizontal straight lines in the strain-life curves. The endurance limit for total strain was obtained according to eq. (4). In general, the endurance limits obtained here must be seen as approximate values as they are based only on a few experimental results of unbroken specimens (runouts).

One of the three equations (1b), (2) and (3) is dependent on the remaining two equations. Therefore a dependency of the constants exists in the form $n' = b/c$ and $K' = \sigma_f' / \epsilon_f'^{b/c}$. This dependency, however, has been neglected in this handbook as it requires a large amount of calculation in the statistical analysis. Comparative studies show that this dependency is sufficiently fulfilled even though the three equations are treated as independent.

Unless noted otherwise, experimental results with plastic strain amplitudes of less than 0.01% have been neglected in the regression analysis, as they mainly

lead to an unsatisfactory description of the life curve according to eqs. (2)-(4) in the low cycle regime. All three life curves for elastic, plastic and total strain are denoted with their appropriate constants in the diagram. The curves are solid in the part where experimental results have been taken into account for regression analysis and dashed in the other parts.

In the diagram of the damage parameter life curve the parameter according to Smith, Watson and Topper [1.4]

$$P_{SWT} = \sqrt{(\sigma_a + \sigma_m) \cdot \epsilon_a \cdot E} \quad (5)$$

was chosen. The analytical description of the damage parameter life curve is obtained by using eqs. (2)-(4) in eq. (5) with $\sigma_m = 0$ leading to

$$P_{SWT}(N) = \sqrt{\sigma_f'^2 \cdot (2N)^{2b} + E \cdot \sigma_f' \cdot \epsilon_f' \cdot (2N)^{(b+c)}} \quad (6)$$

For reasons of uniformity, datasets with experimental results $\epsilon_m \neq 0$ and $\sigma \neq 0$ were treated as if the regression line had been evaluated for $\sigma_m \neq 0$. From the idea that P_{SWT} accounts for mean stresses, P_{SWT} -life curves evaluated from the experimental results with $\sigma_m = 0$ should be plotted into the diagrams with experimental results $\sigma_m \neq 0$, leading to better coincidence between life curve and experiments.

For uniformity, the experimental results for high and low temperatures are presented in a P_{SWT} diagram as well. How far Smith, Watson and Topper's parameter is valid for high and low temperatures has not yet been proven.

The criteria for the solid and dashed part of the curves are the same as for the strain life curves. The endurance limit obtained by maximum likelihood was calculated according to eq. (5) and is indicated in the plot.

The results of stress- and strain-controlled constant amplitude tests are listed on the third and if necessary on the fourth page, specifying the following:

- specimen number
- stress amplitude
- mean stress
- amplitude of total strain
- number of cycles

Unless stated otherwise, stresses and strains are noted in the data sheet for stabilized material behaviour or half failure life.

Blanks in the data sheets indicate that the information was not given in the literature referred to.

Literature

- [1.1] Manson S.S.
Behavior of Materials Under Conditions of Thermal Stress
NACA TN-2933, 1953
- [1.2] Coffin L.F. Jr.
A Study of the Effects of Cyclic Thermal Stresses on a Ductile Metal
Trans. ASME, vol. 76, 1954, pp. 931-950
- [1.3] ASTM E 606-80
Constant-Amplitude Low-Cycle Fatigue Testing
Annual Book of ASTM Standards, Section 3, 1986, pp. 656 - 673
- [1.4] Smith K.N., Watson P., Topper T.H.
A Stress-Strain Function for the Fatigue of Metals
Journal of Materials, IMLSA, Vol. 5, No. 4, 1970, pp. 767-778
- [1.5] Manson S.S.
Fatigue: A Complex Subject - Some Simple Approximations
Experimental Mechanics, Vol. 5, 7, 1965, pp. 193-226
- [1.6] Morrow J.D.
Cyclic Plastic Strain Energy and Fatigue of Metals
ASTM STP 378, 1965, pp. 45-87
- [1.7] ASTM E 739-80
Statistical Analysis of Linear or Linearized Stress-Life (S-N) and
Strain-Life (ϵ -N) Fatigue Data
Annual Book of ASTM Standards, Section 3, 1986, pp. 741 - 746
- [1.8] Spindel J.E., Haibach E.
Some Considerations in the Statistical Determination of the Shape of
S-N Curves
Statistical Analysis of Fatigue Data, ASTM STP 744, 1980, pp. 89 -
113

Nomenclature

A_5	elongation related to 5x diameter of specimen
A_{25}	elongation related to 25x diameter of specimen
b	fatigue strength exponent
c	fatigue ductility exponent
E	Young's modulus
ϵ	strain
ϵ_f	true fracture strain
ϵ_f'	fatigue ductility coefficient
K	monotonic hardening coefficient
K'	cyclic hardening coefficient
N	number of cycles until rupture
N_i	number of cycles until crack initiation
N_T	number of cycles for $\epsilon_a, c = \epsilon_{a,p}$ (transition point)
n	monotonic hardening exponent
n'	cyclic hardening exponent
ν	Poisson's ratio
P_{SWT}	damage parameter according to Smith, Watson and Topper
R	stress ratio
R_m	ultimate tensile strength
$R_{p0.2}$	monotonic 0.2% proof stress
$R'_{p0.2}$	cyclic 0.2% proof stress
σ	stress
σ_f	true fracture stress
σ_f'	fatigue strength coefficient
T_σ	$\sigma_{a,10\%}/\sigma_{a,90\%}$ scatter ratio of stress amplitudes for 10% and 90% probability of survival
$T_{\epsilon p}$	$\epsilon_{a,10\%}/\epsilon_{a,90\%}$ scatter ratio of plastic strain amplitudes for 10% and 90% probability of survival
Z	reduction of area

Indexes:

a	amplitude (semi range)
e	elastic
g	value at $2 \cdot 10^6$ cycles
m	mean value
p	plastic

Literature (Data Sources)

- [2.1] Klee S.
Das zyklische Spannungs-Dehnungs- und Bruchverhalten verschiedener Stähle
Veröffentlichungen des Instituts für Statik und Stahlbau, No. 22, 1973, TH Darmstadt
- [2.2] Traiser H.
Verformungsverhalten und mikrostrukturelle Veränderungen normalisierter Kohlenstoffstähle bei dynamischer Beanspruchung unter besonderer Berücksichtigung des spannungsmechanischen und oberflächentechnischen Größeneinflusses
PhD-Thesis, TH Darmstadt, 1981
- [2.3] Sonsino C.M., Diefenbach W.
Elasto-plastisches Schwingfestigkeitsverhalten von Ck 45 vergütet
LBF-Einzelbericht 2771-4.2 Juli 1978
- [2.4] Boller Chr., Heuler P., Seeger T.
Buxbaum O., Oppermann H., Köbler H.-G., Schütz D.
Vergleich der Lebensdauervorhersage nach dem Kerbgrundkonzept und dem Nennspannungskonzept
Report FD 5/1983, Fachgebiet Werkstoffmechanik, TH Darmstadt, Fraunhofer-Institut für Betriebsfestigkeit (LBF), Darmstadt
- [2.5] Veith H.
Zum Spannungs-Dehnungs-Verhalten von Baustählen bei Wechselbeanspruchung
BAM-Berichte Nr. 8, Nov. 1971, Berlin
- [2.6] Reik W., Mayr P., Macherauch E.
Untersuchungen zum Schwingfestigkeitsverhalten von Ck 45
EGKS research program, final report, part B, 1979
- [2.7] Nowack H., Trautmann K.H.
non published information
- [2.8] Yoshida S., Kanazawa K., Yamaguchi K., Kobayashi K., Sato M., Suzuki N., Shiohara M.
Elevated-Temperature Fatigue Properties of Engineering Materials Part III
Transactions of the Nat. Research Inst. f. Metals, Tokyo, 1978
- [2.9] NRIM Fatigue Data Sheet No. 38
Nat. Research Inst. f. Metals, Tokyo, 1984

- [2.10] NRRM Fatigue Data Sheet No. 39
Nat. Research Inst. f. Metals, Tokyo, 1984
- [2.11] NRRM Fatigue Data Sheet No. 22
Nat. Research Inst. f. Metals, Tokyo, 1980
- [2.12] Luft G.
Zeitfestigkeitsverhalten von Stählen
Techn.-wissenschaftl. Berichte, MPA Stuttgart (1968), Heft 68-02
- [2.13] Wiemann W., Reiermann D.
non published information
- [2.14] Schmalenbach E.-W.
Wechselverformungsuntersuchungen an Kerb- und Biegeproben äquivalenter Geometrie
PhD-Thesis, TU Karlsruhe, 1975
- [2.15] Mitchel M.R., Meyer M.E., Nguyen N.Q.
Fatigue Considerations in Use of Aluminum Alloys
Proc. of the SAE Fatigue Conference, Dearborn Mich., 1982, pp. 249 - 272
- [2.16] Prowatke G.
Zum zyklischen Werkstoffgesetz des Schiffbaustahls 09 G 2
Schiffbauforschung, 21 1/1982, pp. 29 - 34, Rostock, GDR
- [2.17] Morrow JoDean
Low Cycle Fatigue Behaviour of Quenched and Tempered SAE 1045 Steel
T.A.M. Report No. 277, Univ. of Illinois, 1965
- [2.18] Mitchell R.M.
Material Characterization of SAE 950XX; Monotonic and Cyclic Stress-Strain Behaviour and Strain-Life Response
FCP Report No. 25, Univ. of Illinois, 1977
- [2.19] Nihei M., Konno T., Iida K.
Prediction of Fatigue Strength under Bending by Use of Hysteresis Energy Concept
Proc. of Nippon Zoosen Gakkai, (in Japanese), 1984, pp. 511 - 521

- [2.20] Fugger T.F. Jr.
Service Load Histories Analyzed by the Local Strain Approach
Report No. 120, Univ. of Illinois, 1985
- [2.21] Richman R.H., Landgraf R.W.
Some Effects of Retained Austenite on the Fatigue Resistance of
Carburized Steel
Metallurgical Transactions A, Vol. 6A, 1975, pp. 955 - 964
- [2.22] Polak J., Klesnil M., Lukas P.
High Cycle Plastic Stress-Strain Response of Metals
Mat. Science and Engineering, 15, 1974, pp. 231 - 237
- [2.23] Pohl K., Mayr P., Macherauch E.
Shape and Structure of Persistent Slip Bands in Iron Carbon Alloys
Proc. of the Symp. "Defects, Fracture and Fatigue", Mount Gabriel,
Canada, 1982
- [2.24] Schwab W.
Ermüdungsverhalten von fließgepressten bauteilähnlichen Proben
Proc. of "Werkstoffermüdung", DVM, Bad Nauheim, 1985
- [2.25] Iida K., Yamauchi T., Satoh M., Takano G.
Fatigue Strength of Electron Beam Welded Joint of Carbon Steel
IIW-Doc. XIII-1201-86, Tokyo, 1986
- [2.26] Paetzold
Beurteilung der Betriebsfestigkeit von Längsspanndurchführungen
auf der Grundlage der örtlichen Dehnung
IfS-Bericht No. 455, Univ. Hamburg, 1985
- [2.27] Pilo
Zum Wechselverformungsverhalten normalisierter unlegierter Stähle
mit Kohlenstoffgehalten von 0.01 bis 1.02 Gew.-%
PhD-Thesis, TU Karlsruhe, 1979
- [2.28] Higashida Y.
Strain Controlled Fatigue Behaviour of Weld Metal and Heat-Affected
Base Metal in A36 and A514 Steel Welds
PhD-Thesis, Univ. of Illinois, 1976