The background of the cover is a complex, abstract composition. On the left side, there is a network diagram consisting of white circles connected by thin white lines, resembling a molecular or biological structure. This network is overlaid on a background of vibrant, colorful circular patterns in shades of green, red, and pink, which look like microscopic views of cells or colloidal particles. The overall effect is a blend of scientific imagery and artistic abstraction.

Ian W. Hamley

Introduction to **Soft Matter**

REVISED EDITION

Synthetic and Biological
Self-Assembling Materials

 **WILEY**

Introduction to Soft Matter – Revised Edition

Synthetic and Biological Self-Assembling
Materials

IAN W. HAMLEY

School of Chemistry, University of Reading, UK



John Wiley & Sons, Ltd

The right of Ian W. Hamley to be identified as the author of this work has been asserted in accordance with sections 77 and 78 of the Copyright, Designs and Patents Act 1988.

Email (for orders and customer service enquiries): cs-books@wiley.co.uk
Visit our Home Page on www.wileyeurope.com or www.wiley.com

All Rights Reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, scanning or otherwise, except under the terms of the Copyright, Designs and Patents Act 1988 or under the terms of a licence issued by the Copyright Licensing Agency Ltd, 90 Tottenham Court Road, London W1T 4LP, UK, without the permission in writing of the Publisher. Requests to the Publisher should be addressed to the Permissions Department, John Wiley & Sons Ltd, The Atrium, Southern Gate, Chichester, West Sussex PO19 8SQ, England, or emailed to permreq@wiley.co.uk, or faxed to (+44) 1243 770620.

Designations used by companies to distinguish their products are often claimed as trademarks. All brand names and product names used in this book are trade names, service marks, trademarks or registered trademarks of their respective owners. The Publisher is not associated with any product or vendor mentioned in this book.

This publication is designed to provide accurate and authoritative information in regard to the subject matter covered. It is sold on the understanding that the Publisher is not engaged in rendering professional services. If professional advice or other expert assistance is required, the services of a competent professional should be sought.

The Publisher and the Author make no representations or warranties with respect to the accuracy or completeness of the contents of this work and specifically disclaim all warranties, including without limitation any implied warranties of fitness for a particular purpose. The advice and strategies contained herein may not be suitable for every situation. In view of ongoing research, equipment modifications, changes in governmental regulations, and the constant flow of information relating to the use of experimental reagents, equipment, and devices, the reader is urged to review and evaluate the information provided in the package insert or instructions for each chemical, piece of equipment, reagent, or device for, among other things, any changes in the instructions or indication of usage and for added warnings and precautions. The fact that an organization or Website is referred to in this work as a citation and/or a potential source of further information does not mean that the author or the publisher endorses the information the organization or Website may provide or recommendations it may make. Further, readers should be aware that Internet Websites listed in this work may have changed or disappeared between when this work was written and when it is read. No warranty may be created or extended by any promotional statements for this work. Neither the Publisher nor the Author shall be liable for any damages arising herefrom.

Other Wiley Editorial Offices

John Wiley & Sons Inc., 111 River Street, Hoboken, NJ 07030, USA
Jossey-Bass, 989 Market Street, San Francisco, CA 94103-1741, USA
Wiley-VCH Verlag GmbH, Boschstr. 12, D-69469 Weinheim, Germany
John Wiley & Sons Australia Ltd, 42 McDougall Street, Milton, Queensland 4064, Australia
John Wiley & Sons (Asia) Pte Ltd, 2 Clementi Loop #02-01, Jin Xing Distripark, Singapore 129809
John Wiley & Sons Ltd, 6045 Freemont Blvd, Mississauga, Ontario L5R 4J3, Canada

Wiley also publishes its books in a variety of electronic formats. Some content that appears in print may not be available in electronic books.

Anniversary Logo Design: Richard J. Pacifico

Library of Congress Cataloguing-in-Publication Data

Hamley, Ian W.

Introduction to soft matter : synthetic and biological self-assembling materials /

Ian W. Hamley. – Rev. ed.

p. cm.

Includes bibliographical references and index.

ISBN 978-0-470-51609-6 (cloth)

1. Polymers–Textbooks. 2. Colloids–Textbooks. 3. Micelles–Textbooks.

4. Liquid crystals–Textbooks. I. Title.

QD381.H37 2007

547'.7–dc22

2007025456

British Library Cataloguing in Publication Data

A catalogue record for this book is available from the British Library

ISBN 978-0-470-51609-6 (H/B)

978-0-470-51610-2 (P/B)

Typeset in 10/13pt Sabon by Aptara, New Delhi, India

Printed and bound in Great Britain by TJ International, Padstow, Cornwall

This book is printed on acid-free paper responsibly manufactured from sustainable forestry in which at least two trees are planted for each one used for paper production.

Introduction to Soft Matter – Revised Edition

Preface to the Revised Edition

The field of soft matter science remains an exciting and fast developing one. Since the first edition of this book there have been advances in several areas and I felt it appropriate to update the book to reflect this. Several other books in the field have also been published recently (as cited in the revised bibliography sections herein), although most, fortunately, do not overlap too much with mine! The main addition to this text is a new chapter on Biological Soft Matter, which adds significantly to the rather cursory discussion of proteins and DNA in the previous edition and introduces some quite cutting-edge topics. I have also added new sections to Chapter 2 on advanced polymeric materials to discuss dendrimers, polyelectrolytes, and electronic and optoelectronic polymers, albeit briefly. The section about the thermodynamics of micellization in Chapter 4 has also been revised. I thank my students who have sat my Physical Chemistry of Soft Matter courses over the years in various guises for critical comments on the previous treatment, and John Wiley & Sons, Ltd for supporting me in this endeavour.

Ian W. Hamley
School of Chemistry,
University of Reading, UK

Preface to the First Edition

This book is largely intended to provide an introduction to colloid chemistry, but I have used the term 'soft matter' to indicate a unified subject that includes aspects of liquid crystal and polymer science not found in existing textbooks on colloid chemistry. General textbooks of physical chemistry either do not cover colloid chemistry at all or fail to give it the space it deserves. There are fewer than a handful of recent books that give a broad coverage of the physical chemistry of soft materials, and these are written at an advanced level. For both these reasons, and also given that existing introductory colloid chemistry texts are mostly getting rather long in the tooth, I felt that a new book in the area offering up-to-date and unified coverage, would be valuable both to students and researchers.

The book has been written primarily for undergraduates taking physical chemistry courses. In Leeds it is a companion book to the final year module 'Physical Chemistry of Condensed Matter'. I hope it will also be of interest to students of physics and materials science taking courses on colloids, polymers, soft condensed matter or complex fluids. It should also serve as a useful introduction and reference for researchers in these areas.

I wish to thank my editors at Wiley for assistance in the production of the book.

IWH
School of Chemistry,
University of Reading, UK

Contents

Preface to the Revised Edition ix

Preface to the First Edition xi

1. Introduction	1
1.1 Introduction	1
1.2 Intermolecular Interactions	3
1.3 Structural Organization	7
1.4 Dynamics	10
1.5 Phase Transitions	11
1.6 Order Parameters	17
1.7 Scaling Laws	18
1.8 Polydispersity	18
1.9 Experimental Techniques for Investigating Soft Matter	19
1.10 Computer Simulation	33
Further Reading	36
2 Polymers	39
2.1 Introduction	39
2.2 Synthesis	41
2.3 Polymer Chain Conformation	44
2.4 Characterization	51
2.5 Polymer Solutions	62
2.6 Amorphous Polymers	76
2.7 Crystalline Polymers	85
2.8 Plastics	93
2.9 Rubber	94
2.10 Fibres	98
2.11 Polymer Blends and Block Copolymers	100

2.12	Dendrimers and Hyperbranched Polymers	102
2.13	Polyelectrolytes	103
2.14	Electronic and Opto-electronic Polymers	105
	Further Reading	106
	Questions	107
3	Colloids	111
3.1	Introduction	111
3.2	Types of Colloids	112
3.3	Forces between Colloidal Particles	114
3.4	Characterization of Colloids	118
3.5	Charge Stabilization	125
3.6	Steric Stabilization	129
3.7	Effect of Polymers on Colloid Stability	133
3.8	Kinetic Properties	134
3.9	Sols	135
3.10	Gels	136
3.11	Clays	137
3.12	Foams	140
3.13	Emulsions	142
3.14	Food Colloids	149
3.15	Concentrated Colloidal Dispersions	155
	Further Reading	157
	Questions	157
4	Amphiphiles	161
4.1	Introduction	161
4.2	Types of Amphiphile	163
4.3	Surface Activity	168
4.4	Surfactant Monolayers and Langmuir–Blodgett Films	173
4.5	Adsorption at Solid Interfaces	177
4.6	Micellization and the Critical Micelle Concentration	180
4.7	Detergency	194
4.8	Solubilization in Micelles	198
4.9	Interfacial Curvature and Its Relationship to Molecular Structure	200
4.10	Liquid Crystal Phases at High Concentrations	204
4.11	Membranes	211
4.12	Templated Structures	215
	Further Reading	218
	Questions	218

5	Liquid Crystals	221
5.1	Introduction	221
5.2	Types of Liquid Crystals	222
5.3	Characteristics of Liquid Crystal Phases	233
5.4	Identification of Liquid Crystal Phases	238
5.5	Orientational Order	246
5.6	Elastic Properties	253
5.7	Phase Transitions in Liquid Crystals	255
5.8	Applications of Liquid Crystals	259
	Further Reading	269
	Questions	269
6	Biological Soft Matter	275
6.1	Introduction	275
6.2	Lipid Membranes	276
6.3	DNA	284
6.4	Proteins	291
6.5	Polysaccharides and Glycoproteins	304
6.6	Macromolecular Assemblies	308
	Further Reading	310
	Questions	311
	<i>Numerical Solutions to Questions</i>	313
	<i>Index</i>	317

1

Introduction

1.1 INTRODUCTION

Mankind has exploited matter in technology through the ages. For many millenia, we relied on materials like wood or metals that were subject to minimal processing to provide useful objects. It is only within a few minutes of midnight on the proverbial human evolutionary clock that materials have been engineered for ultimate applications based on a deep understanding of molecular properties. Considering substances that have been engineered in a controlled or tailored manner, the nineteenth century was the age of iron and steel. The twentieth century saw the development of new types of engineered materials, especially polymers, which in the form of plastics have, in many applications, usurped many of the traditional 'hard' materials. This is not to forget the emergence of an important class of inorganic material, semiconductors, in the second half of this century. These are, of course, the basis for the second industrial revolution, that of information technology. However, it seems fair to say that many properties of hard matter are now well understood whereas we are still on the learning curve with soft matter. For example, inspired by nature, we are only just beginning to be able to engineer complex structures formed by biopolymers or to exploit nanotechnology to make devices based on self-organization of polymers. In our new millennium it seems safe to predict the continued importance of soft materials, engineered in ways we can as yet only dream of.

The idea of a unified approach to 'soft materials' has only gained ground recently. It is an interdisciplinary subject, taking in aspects of physics, chemistry and materials science, but also of biochemistry or (chemical, mechanical) engineering in specific cases. A consequence of this

interdisciplinarity is that, unfortunately, the subject is not considered in conventional textbooks on physics, physical chemistry or materials science, often being neglected entirely or covered in an inadequate manner. The purpose of this book is to 'fill the gap', by providing an up-to-date introductory summary of the thermodynamics and dynamics of soft materials. In each of the six chapters, the basic physical chemistry is covered first, prior to an outline of applications. The material is presented in a coherent fashion across the book. Equations have been kept to the minimum number that capture important relationships. Derivations are included, where they illustrate thermodynamical or statistical mechanical principles in action. The derivation of the Flory-Huggins theory in Section 2.5.6 or of the thermodynamics of micellar equilibria in Section 4.6.5 are good examples. Soft materials are important in many products, such as detergents, paints, plastics, personal care products, foods, clays, plastics and gels. Such uses of soft materials are exemplified throughout this book.

In this book we consider soft materials under the headings of polymers (Chapter 2), colloids (Chapter 3), amphiphiles (Chapter 4), liquid crystals (Chapter 5) and biological soft materials (Chapter 6). The distinctions between these systems are often not strong. For example, amphiphiles in solution and some aspects of polymer science are often considered in books on colloid chemistry. However, here we treat them separately since they are technologically important enough to merit detailed consideration on their own. The chapter on liquid crystals is in fact focused on one class of material, thermotropic liquid crystals, where phase transitions are thermally driven. However, a different class of liquid crystal phase is formed in amphiphile solutions, where concentration is also a relevant variable. These are termed lyotropic liquid crystal phases and are discussed in Chapter 4.

There are a number of texts that deal with aspects of the subjects covered in this book. General texts in the area include those by Evans and Wennerström, Hunter, Larson and Shaw (see Further Reading at the end of the chapter). Detailed textbooks for background reading on each topic are listed in the Further Reading section that follows each chapter. In Chapter 2, polymer science is outlined in a particularly concise form, and after the fundamentals are introduced, attention is paid to applications of polymers in the latter part of the chapter. There are quite a number of monographs concerned with colloids. However, many of these are not suitable for use as undergraduate textbooks. Thus, Chapter 3 fulfills a particularly useful function in providing an up-to-date introduction to the essential physical chemistry. Also emphasized are applications of colloids and colloids in everyday life, such as in foods. Chapter 4 summarizes the important aspects underpinning the self-assembly of amphiphiles, i.e. surfactants and lipids. The action of surfactants as detergents is also considered and the importance of lipids in

cell membranes is discussed. Chapter 5 is concerned with thermotropic liquid crystals. Chapter 6 is focused on aspects of self-assembly of biological soft materials. Recommended texts for background reading on these subjects are listed in the Further Reading sections.

In this chapter, intermolecular forces that are the basis of self-assembly are considered in Section 1.2. Section 1.3 outlines common features of structural ordering in soft materials. Section 1.4 deals similarly with general considerations concerning the dynamics of macromolecules and colloids. Section 1.5 focuses on phase transitions along with theories that describe them, and the associated definition of a suitable order parameter is introduced in Section 1.6. Scaling laws are defined in Section 1.7. Polydispersity in particle size is an important characteristic of soft materials and is described in Section 1.8. Section 1.9 details the primary experimental tools for studying soft matter and Section 1.10 summarizes the essential features of appropriate computer simulation methods.

1.2 INTERMOLECULAR INTERACTIONS

The term ‘soft’ matter originates from macroscopic mechanical properties. We mean here materials such as colloids, surfactants, liquid crystals, certain biomaterials and polymers in the melt or solution. Many soft materials can be induced to flow under certain conditions. This weak ordering results from the lack of three-dimensional atomic long-range order found in a crystalline solid. Nevertheless, there is always a degree of local order at least as great as that in a liquid. From the viewpoint of kinetic energy, a crude distinction between ‘soft’ materials and ‘hard’ ones can be made on the basis that the molecular kinetic energy for the former is close to $k_{\text{B}}T$, whereas for the latter it is much less than $k_{\text{B}}T$ (when the temperature is near ambient). Here we consider the intermolecular forces responsible for the ordering of soft materials. Our purpose is not to provide a detailed description of these forces, since this is dealt with in many physical chemistry textbooks (for example Atkins, 2006). Here we briefly outline the essential results, especially in the context of self-assembly in soft matter, which is the subject of this book.

The forces between molecules are a balance of repulsive interactions at short distances and attractive interactions that predominate over larger length-scales. This is illustrated by the curve of potential energy as a function of intermolecular separation in Fig. 1.1. We will now consider the origin of the repulsive and attractive forces. Then we consider Coulombic forces since ions are present in solution in many colloid and surfactant systems, and in this case interactions between charged species predominate.




Figure 1.1 Typical curve of potential energy versus separation of two molecules or atoms. At short distances, repulsive interactions predominate, whilst attractive forces act over a longer range

Repulsive interactions are important when molecules are close to each other. They result from the overlap of electrons when atoms approach one another. As molecules move very close to each other the potential energy rises steeply, due partly to repulsive interactions between electrons, but also due to forces with a quantum mechanical origin in the Pauli exclusion principle. Repulsive interactions effectively correspond to steric or excluded volume interactions. Because a molecule cannot come into contact with other molecules, it effectively excludes volume to these other molecules. The simplest model for an excluded volume interaction is the hard sphere model. The hard sphere model has direct application to one class of soft materials, namely sterically stabilized colloidal dispersions. These are described in Section 3.6. It is also used as a reference system for modelling the behaviour of simple fluids. The hard sphere potential, $V(r)$, has a particularly simple form:

$$V(r) = \begin{cases} \infty & \text{for } r \leq d \\ 0 & \text{for } r > d \end{cases} \quad (1.1)$$

where d is the diameter of the hard sphere. The ordering of hard spheres depends only on their volume fraction. The phase diagram has been obtained by computer simulations and experiments on sterically stabilized colloid particles, as discussed in Section 3.6.

The hard sphere model is based on the excluded volume of spherical particles. An excluded volume theory has been developed to account for the orientational ordering of liquid crystal molecules, assuming them to be hard rods. This is the Onsager theory and its variants, outlined in Section 5.5.2. Excluded volume interactions influence the conformation of polymer chains. The conformation of an ideal chain is described by a random walk. However,

in this case the chain can cross itself, i.e. it has no excluded volume. Under certain circumstances a polymer chain can behave as if this was the case (see Section 2.3.2). However, it is more usual for excluded volume interactions to lead to a self-avoiding walk, which produces a more extended conformation than that of a random walk (Section 2.3.2).

Because there are no attractive interactions in the potential, the hard sphere model does not describe the forces between molecules very well. More realistic potentials include an attractive contribution, which usually varies as $-1/r^6$ (as discussed shortly) as well as a repulsive term. The latter is chosen to vary as $1/r^n$, with $n > 6$, to ensure that repulsions dominate at short distances, $n = 12$ often being assumed. This combination of attractive and repulsive terms defines the Lennard-Jones (12,6) potential:

$$V(r) = 4\varepsilon \left[\left(\frac{r_0}{r} \right)^{12} - \left(\frac{r_0}{r} \right)^6 \right] \quad (1.2)$$

Here ε is the depth of the potential energy minimum and $2^{1/6}r_0$ is the intermolecular separation corresponding to this minimum. This potential has a form similar to that shown in Fig. 1.1. It is often used as a starting point for modelling intermolecular interactions, for example it can be chosen as the intermolecular potential in computer simulations (see Section 1.10). It is not completely realistic, though, because for example it is known that the $1/r^{12}$ form is not a good representation of the repulsive potential. An exponential form $\exp(-r/r_0)$ is better because it reproduces the exponential decay of atomic orbitals at large distances, and hence the overlap which is responsible for repulsions.

Attractive interactions in uncharged molecules result from van der Waals forces, which arise from interactions between dipoles. A molecule has a dipole moment if it contains two opposite charges of magnitude q , separated by some distance r . Such a molecule is said to be polar. The dipole moment is then defined by $\mu = qr$. Dipole moments of small molecules are usually about 1 debye (D), where $1\text{D} = 3.336 \times 10^{-30} \text{ C m}$. Some molecules, such as H_2O , possess a permanent dipole moment due to charge separation resulting from the electro-negativity of the oxygen atom. Dipolar molecules can also induce dipole moments in other molecules producing dipole-induced dipole forces. The potential energy between two dipoles can be calculated by summing up the Coulomb potential energy between each of the four charges. Recall that the Coulomb potential energy is given by

$$V(r) = \frac{q_1 q_2}{4\pi \varepsilon_0 r} \quad (1.3)$$

where r is the distance between charges q_1 and q_2 and ϵ_0 is the vacuum permittivity.

Considering two parallel dipoles, the potential can be shown to vary as $1/r^3$. However, if the dipoles are freely rotating, the potential varies as $1/r^6$. Further details of the derivations of these functional forms are provided by Atkins (2006). Here we have only discussed the dependence of the potential on r ; all prefactors are omitted. This type of relationship is an example of a scaling law, discussed in more detail in Section 1.7.

Most molecules are non-polar. It is evident, however, that there must be attractive van der Waals interactions between such molecules in order that condensed phases, such as those exhibited by liquid hydrogen or argon at low temperature, can exist. Molecules without a permanent dipole moment can possess an instantaneous dipole moment due to fluctuations in the atomic electron distribution. These fluctuating dipoles can induce dipoles which create a transient electric field that can polarize nearby molecules, leading to an induced dipole. Such induced dipole–induced dipole forces create dispersion interactions, also known as London interactions. It is again found that the potential varies as $1/r^6$. In other words, for both freely rotating dipole–dipole and induced dipole–induced dipole interactions, the attractive potential takes the form

$$V(r) = -\frac{C}{r^6} \quad (1.4)$$

although the term C is different for the two types of interaction (further details are provided by Atkins, 1998, for example). This explains why the attractive contribution to the total potential is often taken to have the $1/r^6$ form, as in the Lennard–Jones (12,6) potential (Eq. 1.2) for example.

Coulombic forces dominate other interactions in systems containing ions. This is because the Coulombic potential energy falls off much more slowly (as $1/r$, Eq. 1.1) than any dipole–dipole interaction. A typical Coulombic potential energy is $\sim 250 \text{ kJ mol}^{-1}$, whereas a van der Waals energy is about 1 kJ mol^{-1} or less.

An important distinction can be made between materials in which the structure comes from intermolecular ordering and those for which it is produced by the ordering of molecular aggregates. Many soft materials, such as colloids and micellar amphiphiles, belong to the latter class. A necessary condition for the formation of such aggregates is the existence of at least two components in the system. Often the second component is water and then *hydrogen bonding* interactions are important. In fact, hydrogen bonding is predominantly a type of dipole–dipole interaction, although there may also

be some covalent character. For amphiphiles in solution, the *hydrophobic effect* drives the formation of micelles. The hydrophobic effect originates in the local structuring of water, which consists of a tetrahedral arrangement of hydrogen-bonded molecules. When an insoluble species such as a hydrocarbon is added to the water, this structure has to accommodate itself around each molecule, which produces a reduction in entropy. This is known as the hydrophobic effect. This structuring effect is reduced when the molecules assemble into micelles. The hydrophobic effect is discussed further in Section 4.6.5. We note here that since the hydrophobic effect has its origin in the entropy associated with local hydrogen bonding of water molecules, it ultimately depends on dipole–dipole forces.

Even in systems where structure results from molecular self-assembly into aggregates, it is forces between molecules that drive the self-assembly process, although these can be between molecules of different types. In one-component systems such as thermotropic liquid crystals, ordering can only result from forces between molecules of the same type. It is difficult to make a quantitative statement about the precise form of the potential for any soft material, other than observing that it will be some combination of repulsive short-ranged contributions and attractive long-range contributions.

1.3 STRUCTURAL ORGANIZATION

There are both common and distinct features in the ordering of different types of soft material. The most important feature in common is that the ordering is generally intermediate between that of a crystalline solid and that of a liquid. This lack of crystalline order leads to the ‘soft’ mechanical response of the materials. There may, however, be partial translational and/or orientational order of molecules due to the formation of a mesophase by a thermotropic liquid crystal or an amphiphile in water. Polymer melts and solutions are also classified as ‘soft materials’, although there is no long-range translational or orientational order. However, these phases are distinguished from conventional liquids due to their high viscosity and/or viscoelasticity. The lack of long-range translational order can be expressed in another way: soft material structures are characterized by numerous defects, for example lattice dislocations or disclinations in liquid crystals (discontinuities in orientational order, Section 5.4.1). These defects have a profound effect on flow behaviour.

Another feature common to the ordering of soft materials is the periodicity of the structures formed, typically in the range 1–1000 nm, which corresponds to ‘nanoscale’ ordering. Another term often employed is ‘mesoscopic’




Figure 1.2 Examples of ordering in soft materials. A nematic liquid crystal has no long-range translational order, but the molecules (here shown as ellipses) are orientationally ordered. The lamellar phase has one-dimensional translational order, the hexagonal phase two-dimensional translational order and cubic phases three-dimensional translational order. The layers in the lamellar phase can be formed from molecules (smectic phase) or amphiphilic bilayers. A hexagonal structure can be formed by disc-like molecules (then being termed columnar phase) or rod-like micelles. The cubic phase shown here is formed by spherical micelles. Bicontinuous cubic structures are also found (see Fig. 4.25d)

ordering. This originates because the length-scale of the structures is intermediate between the microscopic (atomic) and macroscopic scales.

The number of symmetry groups of possible mesophases is restricted. Many types of soft material form structures of the same symmetry, although the molecular ordering may differ. The nematic phase (Section 5.2.2) possesses no long-range translational order, i.e. the molecular order is locally liquid-like. However, there is long-range orientational order (Fig. 1.2). Nematic phases are formed by particles ranging from small organic molecules ($\sim 2\text{--}3\text{ nm}$ long), such as those used in liquid crystal displays, up to long macromolecules, such as rod-like tobacco mosaic virus ($\sim 300\text{ nm}$ long).

The simplest structure with translational order is a one-dimensional layered structure (Fig. 1.2). In thermotropic liquid crystals, there are a number of such smectic phases formed by molecules in a weakly layered arrangement (Section 5.2.2). Amphiphiles also form smectic phases, but they are usually